Formulation:

Project No.: EA16335

## amec foster wheeler

## Attn: Mr. Joe Filice R.E.T.

To: Alberta Transportation Technical Standards Branch 2nd Floor, Twin Atria Building 4999 - 98 Ave Edmonton, AB T6B 2X3 Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure 5671 - 70 Street Edmonton, AB Canada T6B 3P6 Tel +1 (780) 436-2152 Fax +1 (780) 377-3599

## Supplier: SHERWIN WILLIAMS

Yellow WB 14-01Y			Tests R	equired					
Lab	Batch	Relative	Viscosity	Non-	Pigment	Date	Date	Date	Applicator and Location
Sample	Number	Density		Volatile	Content	Sampled	Received	Reported	
Number				Content					
	2016	(25/25°C)	(Krebs)	(%)	(%)	2016	2016	2016	
B70	VR2645VN	1.627	74.4*			Jun-23	Jun-28	Jun-28	Ledcor/AAA Paving, CON # 12339, Hwy 1:04/:06
B102	VR2645VN	1.645	79.5	79.1	62.1	Jul-21	Jul-21	Jul-25	AAA Striping, Re-test for AT 12339, Wetaskiwing yard tote
			Toleranc	e Limits					
2015	14-01Y	1.682	80.8	79.9	62.7				
Tolerance Limits				± 2%	± 2%				
		± 0.05	± 5	absolute	absolute				
Upper Limit		1.732	85.8	81.9	64.7				
Lower Limit		1.632	75.8	77.9	60.7				

\* Indicates result outside tolerance limits.

Test not Required by AT

PER

DATE

Reviewed By:

Reporting of these results constitutes a testing service only. Engineering Interpretation or evaluation of the test results is provided only on written request.