

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16335

Attn: Mr. Joe Filice R.E.T.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation:		Supplier: <b>ENNIS</b>							
White Acetone 986061		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Date Sampled	Date Received	Date Reported	Applicator and Location
<b>B79</b>	CPP1604W0448	1.398	71.4*			Jun-27	Jul-4	Jul-5	Stambottas, 240045 Frontier Place SE, Rolley View County, AB via Gun
Tolerance Limits									
	<b>986061</b>	<b>n/a</b>	<b>n/a</b>	<b>n/a</b>	<b>n/a</b>				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.5	90	76.0	57.5				
Lower Limit		1.35	75	71.0	52.0				

\* Indicates result outside tolerance limits.



Test not Required by AT

PER \_\_\_\_\_

DATE \_\_\_\_\_

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.