

TRAFFIC PAINT TEST REPORT

Project No.: EA16335



Attn: Mr. Joe Filice R.E.T.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: ENNIS							
Yellow Acetone 986063		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Date Sampled	Date Received	Date Reported	Applicator and Location
	2016	(25/25°C)	(Krebs)	(%)	(%)	2016	2016	2016	
B40	CPP1605Y0563	1.374	76.8	72.0	50.0	Jun-9	Jun-17	Jun-22	Carmacks, Deerfoot Trail
Tolerance Limits									
	986063	n/a	n/a	n/a	n/a				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.45	90	73.0	53.0				
Lower Limit		1.35	75	68.0	48.0				

* Indicates result outside tolerance limits.

 Test not Required by AT

 PER: _____
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.