

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16048



Attn: Mr. Joe Filice R.E.T.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

| Formulation:<br>White SB EF-71-0001 |                   | Supplier: SHERWIN WILLIAMS |             |                  |                                |                             |                    |                 |                  |                  |   |
|-------------------------------------|-------------------|----------------------------|-------------|------------------|--------------------------------|-----------------------------|--------------------|-----------------|------------------|------------------|---|
| Lab<br>Sample<br>Number             | Batch<br>Number   | Relative<br>Density        | Viscosity   | Colour           | Dry to<br>Traffic<br>(Minutes) | Non-<br>Volatile<br>Content | Pigment<br>Content | Date<br>Sampled | Date<br>Received | Date<br>Reported | Applicator and Location   |
|                                     |                   | (25/25°C)                  | (Krebs)     |                  | Batch                          | (%)                         | (%)                |                 |                  |                  |   |
| <b>B1</b>                           | CPP1404W0182      | 1.485*                     | 90.6*       |                  |                                |                             |                    | Mar-10          | Mar-18           | Mar-23           | Provincial, Hwy 22:30, west of Jct Hwy 22(s) South of Drayton Valley, Contract No.10431 |
|                                     |                   |                            |             |                  |                                |                             |                    |                 |                  |                  |   |
|                                     |                   |                            |             |                  |                                |                             |                    |                 |                  |                  |   |
|                                     |                   |                            |             |                  |                                |                             |                    |                 |                  |                  |   |
| Tolerance Limits                    |                   |                            |             |                  |                                |                             |                    |                 |                  |                  |   |
| <b>2015</b>                         | <b>EF-71-0001</b> | <b>1.388</b>               | <b>76.8</b> | <b>N/A</b>       | <b>N/A</b>                     | <b>70.1</b>                 | <b>51.2</b>        |                 |                  |                  |   |
| Tolerance Limits                    |                   | ± 0.05                     | ± 5         | Match<br>505-308 | ± 20%<br>Formulation           | ± 2%<br>absolute            | ± 2%<br>absolute   |                 |                  |                  |   |
| Upper Limit                         |                   | 1.438                      | 81.8        |                  |                                | 72.1                        | 53.2               |                 |                  |                  |   |
| Lower Limit                         |                   | 1.338                      | 71.8        |                  |                                | 68.1                        | 49.2               |                 |                  |                  |   |

\* Indicates result outside tolerance limits.



Test not Required by AT

PER \_\_\_\_\_

DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.