



SPECIFICATIONS FOR GRAVEL LINING MATERIAL

Gravel ditch lining may be pit run gravel screened where necessary to conform to the following sizes:

Passing 6" square opening	100 %
Passing 3" square opening	40-60 %
Passing 1" square opening	25-40 %
Passing a #10 Standard sieve	0-25 %

- Compaction shall be accomplished by 4 or more passes with an approved roller or other compaction equipment approved by the Engineer.

TYPICAL CROSS SECTION SHOWING GRAVEL DITCH LINING REQUIREMENTS

DWG. N^oS-721

APPROVED JUNE 20, 1960

W. E. McNamee
CHIEF BRIDGE ENGINEER

S-721

