## TRAFFIC PAINT TEST REPORT

Project No.: EA16335

wood.

Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions

5671 - 70 Street Edmonton, AB Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Formulation: White Acetone 986061		S	upplier:	ENNIS					
		Tests Required							
Lab Sample Number	Batch Number 2019	Relative Density (25/25°C)	Viscosity (Krebs)	Non- Volatile Content (%)	Pigment Content (%)	Date Sampled 2019	Date Received 2019	Date Reported 2019	Applicator and Location
B1	CPP1810W1713	1.494	91.2*	75.9	58.6*	May-11	May-17	Jun-3	Lahrmann Hwy 40:10 to 12
B3	CPP1810W1713	1.483	84.5	75.8	58.4*	May-14	May-23	Jun-3	Line King Hwy 2:04
		Tolerance Limits							
	986061	n/a	n/a	n/a	n/a				
Tole	Tolerance Limits			± 2%	± 2%				
			± 5	absolute	absolute				
U	Upper Limit		90	76.0	57.5				
L	Lower Limit		75	71.0	52.0				

Note: White Paint Formulation 986061 - , batch number - CPP1810W1806, did not match submitted manufacturer's samples.

\* Indicates result outside tolerance limits.

Test not Required by AT

PER

3/Jun/19

Reviewed By:

Reporting of these results constitutes a testing service only.

Engineering Interpretation or evaluation of the test results is provided only on written request.