

TRAFFIC PAINT TEST REPORT

Project No.: EA16335



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3


Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: ENNIS							
Yellow Acetone 986063		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Date Sampled 2019	Date Received 2019	Date Reported 2019	Applicator and Location
	2019								
B2	CPP1810Y1777	1.427	87.6	75.7*	54.5*	May-11	May-17	Jun-3	Lahrmann Hwy 40:10 to 12
B4	CPP1810Y1777	1.468*	90	77.0*	56.0*	May-14	May-23	Jun-3	Line King Hwy 2:04
Tolerance Limits									
	986063	n/a	n/a	n/a	n/a				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.45	90	75.0	53.0				
Lower Limit		1.35	75	70.0	48.0				

* Indicates result outside tolerance limits.

Note: Yellow Paint Formulation 986063 - , batch number - CPP1810Y1777, did not match submitted manufacturer's samples.

 Test not Required by AT

PER:  3/Jun/19
 DATE

Reviewed By: 

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.