

TRAFFIC PAINT TEST REPORT

Project No.: EA16335




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: Cloverdale							
White Acetone Cloverdale		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Date Sampled	Date Received	Date Reported	Applicator and Location
	2020	(25/25°C)	(Krebs)	(%)	(%)	2020	2020	2020	
B101	W20C5228*	1.545	84.5*	75.6	59.5	Aug-24	Aug-25	Sep-1	Line West Hwy 28:06 Fron Jct Hwy 28:06 To Hwy 831:06/08 Km 16:289 To Km 16:800
Tolerance Limits									
	70291	1.537	91.8	75.5	58.1				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.587	96.8	77.5	60.1				
Lower Limit		1.431	86.8	73.5	56.1				

Note: Yellow Paint Formulation 70291 - , batch number - W20C5228, did not match submitted manufacturer's samples.

* Indicates result outside tolerance limits.
 Test not Required by AT

PER: _____ Sep-1
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.