

TRAFFIC PAINT TEST REPORT

Project No.: EA16335




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: Cloverdale								
Yellow Acetone Cloverdale		Tests Required								
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Date Sampled 2020	Date Received 2020	Date Reported 2020	Applicator and Location	
B102	W19G2852*	1.487	89.1	74.8	57.2	Aug-24	Aug-25	Sep-1	Line West Hwy 28:06 Fron Jct Hwy 28:06 To Hwy 831:06/08 Km 16:289 To Km 16:800	
Tolerance Limits										
	70292	1.481	89.2	74.0	55.9					
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute					
Upper Limit		1.531	94.2	76.0	57.9					
Lower Limit		1.431	84.2	72.0	53.9					

Note: Yellow Paint Formulation 70292 - , batch number - W19G2852, did not match submitted manufacturer's samples.

* Indicates result outside tolerance limits.
 Test not Required by AT

PER: _____ Sep-1
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.