



**TRAFFIC PAINT TEST REPORT**

Project No.: EA16335




Attn: Rishi Adhikari, P.Eng.



To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation:		Supplier: ENNIS							
White Acetone 986061		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Date Sampled 2019	Date Received 2019	Date Reported 2019	Applicator and Location
<b>B133</b>	CPP1903W0193	1.458	86.4	75.0	54.9	Jun-9	Sep-3	Sep-6	Contract No: 12990 (flatiron construction)
<b>Tolerance Limits</b>									
	<b>986061</b>	<b>n/a</b>	<b>n/a</b>	<b>n/a</b>	<b>n/a</b>				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.5	90	76.0	57.5				
Lower Limit		1.35	75	71.0	52.0				

**Note: White Paint Formulation 986061 - , batch number - CPP1810W1806, did not match submitted manufacturer's samples.**

\* Indicates result outside tolerance limits.  
 Test not Required by AT

PER  6/Sep/19  
 DATE  
 Reviewed By: 

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

