

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: White Acetone 986061		Supplier: ENNIS							
Tests Required									
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density	(Krebs)	Volatile Content (%)	Content (%)	Touch	Sampled	Received	
	20201	(25/25°C)					2021	2021	
B1	CPP2102W0064	1.465	86.1	72.5	55	1.4	May-25	May-11	CANA Hwy 22:14 Contract Nuber : 21613
Tolerance Limits									
	986061	N/A	N/A	N/A	N/A				
Tolerance Limits									
Upper Limit									
Lower Limit									

* Indicates result outside tolerance limits.



Test not Required by AT

Note: White Paint Formulation:
986061, Manufacture batch# CPP2102W0064
density was 1.466 and Viscosity 83.5

PER  May-14
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: ENNIS							
White Acetone 986061		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density	(Krebs)	Volatile Content (%)	Content (%)	Touch	Sampled	Received	
	20201	(25/25°C)					2021	2021	
B16	CPP2006W0676	1.427	83.8	72.7	55.3	1.4	May-30	Jun-14	AAA Stripping Line Painting Hwy 33 :12
B18	CPP2008W1173	1.430	95.2*	71.9	54.0	1.7	Jun-6	Jun-14	AAA Stripping Line Painting Hwy 33 :12
Tolerance Limits									
	986061	N/A	N/A	N/A	N/A				
Tolerance Limits			± 5	± 2% absolute	± 2% absolute				
Upper Limit			90	76.0	57.5				
Lower Limit		1.35	75	71.0	52.0				

Note: White Paint Formulation:
 986061, Manufacture batch# CPP2102W0064
 density was 1.466 and Viscosity 83.5

* Indicates result outside tolerance limits.



Test not Required by AT

PER _____ Jun-29
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: ENNIS							
White Acetone 986061		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density	(Krebs)	Volatile Content	Content	Touch	Sampled	Received	
	20201	(25/25°C)	(Krebs)	(%)	(%)		2021	2021	
B28	CPP2105W0452	1.453	80.3	73.5	56.2	1.4	Jun-14	Jun-17	Main Roads Deerfoot Lane1 SB+NB
Tolerance Limits									
	986061	N/A	N/A	N/A	N/A				
Tolerance Limits			± 5	± 2% absolute	± 2% absolute				
Upper Limit			90	76.0	57.5				
Lower Limit		1.35	75	71.0	52.0				

Note: White Paint Formulation:
 986061, Manufacture batch# CPP2102W0064
 density was 1.466 and Viscosity 83.5

* Indicates result outside tolerance limits.

Test not Required by AT

PER _____ DATE Jul-19

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: ENNIS							
White Acetone 986061		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density		Volatile Content	Content	Touch	Sampled	Received	
		(25/25°C)	(Krebs)	(%)	(%)		2021	2021	
B73	CPP2105W0355	1.461	84.3	74.6	57.4	1.4	Jul-13	Aug-12	LaFrentz Hwy 43 : 06 Sampler Jesse Kasouf 780-618-1685
Tolerance Limits									
	986061	N/A	N/A	N/A	N/A				
Tolerance Limits			± 5	± 2% absolute	± 2% absolute				
Upper Limit			90	76.0	57.5				
Lower Limit		1.35	75	71.0	52.0				

Note: White Paint Formulation:
 986061, Manufacture batch# CPP2102W0064
 density was 1.466 and Viscosity 83.5

* Indicates result outside tolerance limits.
 Test not Required by AT

PER  Aug-24
 DATE
 Reviewed By: 

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: ENNIS							
White Acetone 986061		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density	(Krebs)	Volatile Content (%)	Content (%)	Touch	Sampled	Received	
	20201	(25/25°C)		(%)	(%)		2021	2021	
B102	CPP2106W0600	1.442	89.2	73.2	56	1.4	Aug-25	Aug-30	Line West Ltd Hwy 22: 16 Contract Number : 21955
B104	CPP2106W0600	1.493	101.5*	76.3	58.2*	1.6	Sep-2	Sep-7	Line West Ltd Hwy 1 : 10 Contract Number : 21955
Tolerance Limits									
	986061	N/A	N/A	N/A	N/A				
Tolerance Limits			± 5	± 2% absolute	± 2% absolute				
Upper Limit			90	76.0	57.5				
Lower Limit		1.35	75	71.0	52.0				

* Indicates result outside tolerance limits.

 Test not Required by AT

PER  Sep-14
 DATE

Reviewed By: 

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: ENNIS							
White Acetone 986061		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density	(Krebs)	Volatile Content (%)	Content (%)	Touch	Sampled	Received	
	20201	(25/25°C)					2021	2021	
B122	CPP2108W0808	1.447	83.6	74.3	56.8	1.4	Sep-21	Sep-23	Main Roads DeerFoot Trail
B135	CPP2108W0901	1.456	103.6*	74.3	56.2	1.7	Sep-9	Oct-1	LaFrentz Hwy 16: 04 Test Section C Contract Number 0019698
B137	CPP2108W0901	1.448	104.0*	73.7	56	1.7	Sep-18	Oct-1	LaFrentz Hwy 16: 04 Test Section D Contract Number 0019698
Tolerance Limits									
	986061	N/A	N/A	N/A	N/A				
Tolerance Limits			± 5	± 2% absolute	± 2% absolute				
Upper Limit			90	76.0	57.5				
Lower Limit		1.35	75	71.0	52.0				

* Indicates result outside tolerance limits.

Test not Required by AT

PER Oct-20
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: ENNIS							
White Acetone 986061		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density	(Krebs)	Volatile Content (%)	Content (%)	Touch	Sampled	Received	
	20201	(25/25°C)					2021	2021	
B155	CPP2109W0955	1.460	94.6*	73.6	56.1	1.6	Oct-18	Sep-22	HWY 12 : 12 Contract Number 21295
Tolerance Limits									
	986061	N/A	N/A	N/A	N/A				
Tolerance Limits			± 5	± 2%	± 2%				
	Upper Limit		90	absolute	absolute				
	Lower Limit	1.35	75	71.0	52.0				

* Indicates result outside tolerance limits.

 Test not Required by AT

PER  Nov-15

DATE

Reviewed By:

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450

wood.Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3


Distribution Addressee: Wood Environment & Infrastructure Solutions
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: ENNIS							
White Acetone 986061		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density	(Krebs)	Volatile Content (%)	Content (%)	Touch	Sampled	Received	
	20201	(25/25°C)	(Krebs)	(%)	(%)		2021	2021	
B160	CPP2109W0955	1.390	71.6*	71.2	52.6	1.3	N/A	Oct-21	AAA Stripping Line Painting Hwy 16A:08 approximately 300 m west of Evansburg, Alberta
Tolerance Limits									
986061		N/A	N/A	N/A	N/A				
Tolerance Limits			± 5	± 2% absolute	± 2% absolute				
Upper Limit			90	76.0	57.5				
Lower Limit		1.35	75	71.0	52.0				

* Indicates result outside tolerance limits.



Test not Required by AT

PER  Nov-24

DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3


Distribution Addressee: Wood Environment & Infrastructure Solutions
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: ENNIS							
White Acetone 986061		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density		Volatile Content	Content	Touch	Sampled	Received	
	20201	(25/25°C)	(Krebs)	(%)	(%)		2021	2021	
B166	CPP2109W0955	1.411	77.8	73.4	54.2	1.4	Oct-14	Oct-21	Line West Ltd Hwy 201: 06 (22X) Contract Number 18602
B168	CPP2109W0955	1.439	83.6	72.8	54.9	1.5	Oct-24	Oct-25	LaFrenz Hwy 15 : 03/04
Tolerance Limits									
	986061	N/A	N/A	N/A	N/A				
Tolerance Limits			± 5	± 2% absolute	± 2% absolute				
Upper Limit			90	76.0	57.5				
Lower Limit		1.35	75	71.0	52.0				

* Indicates result outside tolerance limits.



Test not Required by AT

PER  Dec-6
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: ENNIS							
White Acetone 986061		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density	(Krebs)	Volatile Content (%)	Content (%)	Touch	Sampled	Received	
	20201	(25/25°C)		(%)	(%)		2021	2021	
B174	CPP2106W0600	1.454	92.7*	74.7	57.3	1.6	Nov-3	Nov-12	Line West Ltd Hwy 2 : 64 Contract Number 12575
B178	CPP2108W0901	1.444	86.0	73.1	56	1.4	Nov-4	Dec-8	LaFrenz Hwy 676
Tolerance Limits									
	986061	N/A	N/A	N/A	N/A				
Tolerance Limits			± 5	± 2% absolute	± 2% absolute				
Upper Limit			90	76.0	57.5				
Lower Limit		1.35	75	71.0	52.0				

* Indicates result outside tolerance limits.

 Test not Required by AT

PER  Dec-13
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.