

TRAFFIC PAINT TEST REPORT

Project No.: EA16335



Attn: Rishi Adhikari, P.Eng.


To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599



Formulation:		Supplier: ENNIS							
Yellow Acetone 986063		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Date Sampled	Date Received	Date Reported	Applicator and Location
B132	CPP1804Y0269	1.427	74.2*	74.6	55.8*	Jun-9	Sep-3	Sep-6	Contract No: 12990 (flatiron construction)
Tolerance Limits									
	986063	n/a	n/a	n/a	n/a				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.45	90	75.0	53.0				
Lower Limit		1.35	75	70.0	48.0				

Note: Yellow Paint Formulation 986063 - , batch number - CPP1810Y1777, did not match submitted manufacturer's samples.

* Indicates result outside tolerance limits.



Test not Required by AT

PER:  6/Sep/19
 DATE
 Reviewed By: 

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

