TRAFFIC PAINT TEST REPORT

Project No.: EA16335



Attn: Mr. Joe Filice R.E.T.

To: Alberta Transportation Technical Standards Branch 2nd Floor, Twin Atria Building 4999 - 98 Ave

Edmonton, AB T6B 2X3

Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure

5671 - 70 Street Edmonton, AB Canada T6B 3P6 Tel +1 (780) 436-2152 Fax +1 (780) 377-3599

Formulation:		Supplier:		ENNIS					
Yellow WB EF-62-0001		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Date	Date	Date	Applicator and Location
Sample	Number	Density		Volatile	Content	Sampled	Received	Reported	
Number				Content					
	2016	(25/25°C)	(Krebs)	(%)	(%)	2016	2016	2016	
B20	CPP1505Y0572	1.539	72.6	77.5	56.7	May-30	Jun-7	Jun-8	Ledcor Alberta Limited, Hwy 666:04 km30, from applicator gun
B22	CPP1505Y0572	1.583	71.8	77.5	56.6	Jun-1	Jun-7	Jun-8	Ledcor Alberta Limited, Hwy 2.68 SBL & NBL btwn 1-5km of Dunvegan Bridge, frm appl. gun
		Tolerance Limits							
2014	EF-62-0001	1.562	75.2	78.3	58.1				
Tolerance Limits				± 2%	± 2%				
		± 0.05	± 5	absolute	absolute				
Upper Limit		1.612	80.2	80.3	60.1				
Lower Limit		1.512	70.2	76.3	56.1				

* Indicates result outside tolerance limits.	
Test not Required by AT	
PER:	
	DATE
Reviewed By:	

Reporting of these results constitutes a testing service only.

Engineering Interpretation or evaluation of the test results is provided only on written request.