

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16335



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation: Yellow WB 985222		Supplier: PPG							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
<b>B48</b>	CPP2106Y0625	1.674	88.4	80.1	62.8	3.4	Jul-19	Jul-28	Lafrentz Hwy 737 CMA 4 East jesse Kasouf 780-618-1685
		Tolerance Limits							
<b>985222</b>									
Tolerance Limits									
Upper Limit									
Lower Limit									

\* Indicates result outside tolerance limits.



Test not Required by AT

Note: Yellow Paint Formulation is not on the Alberta Transportation approved list.

PER: \_\_\_\_\_ 23-Aug-22  
 DATE  
 Reviewed By:  \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16335



Attn: Rishi Adhikari, P.Eng.


To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation: Yellow WB 985222		Supplier: PPG							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B90	GPP2106Y0625	1.711	92.8*	80.7	63.5	3.6	Sep-6	Sep-15	Lafrentz Hwy 753 : 02 Con# 22686 Sampler Ali Joyo
<b>Tolerance Limits</b>									
985222									
Tolerance Limits									
Upper Limit									
Lower Limit									

Note: Yellow Paint Formulation is not on the Alberta Transportation approved list.

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ 26-Sep-22  
 DATE  
 Reviewed By:  \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16335




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation: Yellow WB 985222		Supplier: PPG							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
<b>B120</b>	CPP2205Y0533	1.699	99.5*	81.4	64.1	2.2	Oct-13	Oct-14	Emcon Hwy 870 : 02 Sampler by: Dwight Rewiga 780-608-5718
		Tolerance Limits							
	<b>985222</b>								
Tolerance Limits									
Upper Limit									
Lower Limit									

**Note: Yellow Paint Formulation is not on the Alberta Transporatations approved list.**

\* Indicates result outside tolerance limits.  
 Test not Required by AT

PER: \_\_\_\_\_ 24-Oct-22  
 DATE  
 Reviewed By:  \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.