

TRAFFIC PAINT TEST REPORT

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: Wood Environment & Infrastructure Solutions

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: White KW-1802		Supplier: ISP							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
B23	151/21	1.716	81.5	76.8	62.9	3.3	Jun-27	Jul-9	AAA Striping Hwy 749 : 2
Tolerance Limits									
2020	KW-1802	1.704	84.3	76.7	65.1				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.754	89.3	78.7	67.1				
Lower Limit		1.654	79.3	74.7	63.1				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ 18-Jul-22
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP E&I Canada Limited

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Formulation: White KW-1802		Supplier: ISP							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
B103	215	1.713	81.2	76.8	65.8	3.5	Sep-28	Sep-30	West-Can Hwy 41:08 Hwy 36:08 and Hwy 36: 10 Con#22757
		Tolerance Limits							
2020	KW-1802	1.704	84.3	76.7	65.1				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.754	89.3	78.7	67.1				
Lower Limit		1.654	79.3	74.7	63.1				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ 12-Oct-22
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP E&I Canada Limited

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Formulation: White KW-1802		Supplier: ISP							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
B123	215	1.734	85.7	77.6	65.6	3.3	Sep-13	Oct-20	AAA Striping Hwy 16:30
2020 KW-1802		1.704	84.3	76.7	65.1				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.754	89.3	78.7	67.1				
Lower Limit		1.654	79.3	74.7	63.1				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ 31-Oct-22
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.