

TRAFFIC PAINT TEST REPORT

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

| Formulation: | | Supplier: ISP | | | | | | | |
|-------------------|--------------|------------------|-----------|----------------------|-----------------|----------------|--------------|---------------|--------------------------|
| White KW-29 | | Tests Required | | | | | | | |
| Lab Sample Number | Batch Number | Relative Density | Viscosity | Non-Volatile Content | Pigment Content | Dry to Traffic | Date Sampled | Date Received | Applicator and Location |
| | 2025 | (25/25°C) | (Krebs) | (%) | (%) | | 2025 | 2025 | |
| B17 | P-7 | 1.604* | 79.0 | 77.2 | 61.5 | 10.5 | Jun-14 | Jun-17 | AAA Hwy 609:02 Con#23732 |
| Tolerance Limits | | | | | | | | | |
| 2023 | KW-29 | 1.676 | 76.2 | 78.6 | 61.7 | 9.1 | | | |
| Tolerance Limits | | ± 0.05 | ± 5 | ± 2% absolute | ± 2% absolute | | | | |
| Upper Limit | | 1.726 | 81.2 | 80.6 | 63.7 | 20 max. | | | |
| Lower Limit | | 1.626 | 71.2 | 76.6 | 59.7 | N/A | | | |

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ 2-Jul-25
DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 818-5351
Tel +1 (780) 818-5355

| Formulation: | | Supplier: | | ISP | | | | | |
|-------------------|--------------|------------------|-----------|----------------------|-----------------|----------------|--------------|---------------|---|
| White KW-29 | | Tests Required | | | | | | | |
| Lab Sample Number | Batch Number | Relative Density | Viscosity | Non-Volatile Content | Pigment Content | Dry to Traffic | Date Sampled | Date Received | Applicator and Location |
| | 2025 | (25/25°C) | (Krebs) | Content (%) | (%) | | 2025 | 2025 | |
| B43 | P-251 | 1.670 | 77.2 | 77.8 | 61.8 | 9.8 | Jul-4 | Jul-16 | AAA Hwy 88:04 from Km 0.000 to Km 20:070 Con# 24539 |
| | | | | | | | | | |
| | | Tolerance Limits | | | | | | | |
| 2023 | KW-29 | 1.676 | 76.2 | 78.6 | 61.7 | 9.1 | | | |
| Tolerance Limits | | ± 0.05 | ± 5 | ± 2% absolute | ± 2% absolute | | | | |
| Upper Limit | | 1.726 | 81.2 | 80.6 | 63.7 | 20 max. | | | |
| Lower Limit | | 1.626 | 71.2 | 76.6 | 59.7 | N/A | | | |

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____

22-Jul-25

DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.