

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: Wood Environment & Infrastructure Solutions


To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: White WB 14251		Supplier: OZARK							
Tests Required									
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Date Sampled	Date Received	Date Reported	Applicator and Location
B141	041919WM0097	1.560	75.8	77.5	61.2	Aug-28	Sep-5	Sep-6	Lafrentz Hwy 689 CMA 4 East
Tolerance Limits									
2019	14251	1.604	77.6	78.0	60.8				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.654	82.6	80.0	62.8				
Lower Limit		1.554	72.6	76.0	58.2				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____

6-Sep-19

DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: Wood Environment & Infrastructure Solutions

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Formulation: White WB 14251		Supplier: OZARK							
Tests Required									
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Date Sampled 2019	Date Received 2019	Date Reported 2019	Applicator and Location
BI47	041919WM0097	1.635	84.0*	80.0	62.3	9/4/2019	9/6/2019	Sep-13	Contract No: 11476 Hwy 43x :03 Grande Praire
Tolerance Limits									
2019	14251	1.604	77.6	78.0	60.8				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.654	82.6	80.0	62.8				
Lower Limit		1.554	72.6	76.0	58.2				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ 13-Sep-19

Reviewed By: _____ DATE

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.