

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Limited

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

To: Alberta Transportation

Technical Standards Branch

2nd Floor, Twin Atria Building

4999 - 98 Ave

Edmonton, AB T6B 2X3

Supplier: **OZARK****Tests Required**

Formulation: White WB 17251B		Tests Required							
Lab Sample Number	Batch Number 2024	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled 2024	Date Received 2024	Applicator and Location
B1	040324WD0041	1.561*	65.0*	71.2*	57.9*	3.5	May-9	May-27	Volker Stevin CMA6 Pincher Creek, AB
Tolerance Limits									
2023	17251B	1.663	82	75.7	62.8				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8				
Lower Limit		1.613	77	73.7	60.8				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: 

30-May-24

DATE

Reviewed By: 

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Formulation:		Supplier: OZARK							
White WB 17251B		Tests Required							
Lab Sample Number	Batch Number 2024	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled 2024	Date Received 2024	Applicator and Location
B3	011624WD0008	1.554*	78.2	75.1	61.3	3.7	May-29	May-30	EMCON Hwy 21:26, 12:611-23:773 CMA9 Sampler Ryan Luider 780-644-2822
B5	011924WD0011	1.613	76.4*	74.5	60.8	3.3	May-27	May-31	Emcon Hwy 2:40 Sampler Athur Kavulok 780-675-2780
Tolerance Limits									
2023	17251B	1.663	82	75.7	62.8				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8				
Lower Limit		1.613	77	73.7	60.8				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____

14-Jun-24

DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Formulation:		Supplier: OZARK							
White WB 17251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Touch	Date Sampled	Date Received	Applicator and Location
	2024	(25/25°C)	(Krebs)	Content (%)	(%)	(Minutes)	2024	2024	
B49	051624WD0079	1.652	80.1	75.6	61.4	3.1	Jul-23	Jul-24	Volker Stevin Medicine Hat Hwy 1:20 CMA23
B51	050224WM0103	1.615	80.1	76.1	62.2	3.4	Jul-19	Jul-24	Volker Stevin Hwy 22:20 CMA514
		Tolerance Limits							
2023	17251B	1.663	82	75.7	62.8	2.5			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8				
Lower Limit		1.613	77	73.7	60.8				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____

6-Aug-24

DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Formulation:		Supplier: OZARK							
White WB 17251B		Tests Required							
Lab Sample Number	Batch Number 2024	Relative Density	Viscosity	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes) (Minutes)	Date Sampled 2024	Date Received 2024	Applicator and Location
		(25/25°C)	(Krebs)						
B63	060424WD0103	1.598*	78.2	75.6	61.0	3.3	Aug-12	Aug-14	Emcon Hwy 55 :12
		Tolerance Limits							
2023	17251B	1.663	82	75.7	62.8	2.5			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8				
Lower Limit		1.613	77	73.7	60.8				

* Indicates result outside tolerance limits.



Test not Required by AT

PER:

19-Aug-24

DATE

Reviewed By:

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT
Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Limited
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Formulation:		Supplier: OZARK							
White WB 17251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Touch	Date Sampled	Date Received	Applicator and Location
	2024	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2024	2024	
B83	062724WD0130	1.632	81.8	75.8	62.0	3.2	Aug-25	Sep-5	Hwy 580:02 CMA514
B87	042324WD0057	1.664	81.8	75.5	61.9	3.1	Aug-23	Sep-5	Volker Stevin Lethbridge AB
B89	052224WD0083	1.655	81.5	75.8	61.5	3.1	Aug-25	Sep-5	Volker Stevin Cardston AB
		Tolerance Limits							
2023	17251B	1.663	82	75.7	62.8	2.5			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8				
Lower Limit		1.613	77	73.7	60.8				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____
Reviewed By: _____
16-Sep-24
DATE

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Formulation:		Supplier: OZARK							
White WB 17251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes) (Minutes)	Date Sampled 2024	Date Received 2024	Applicator and Location
	2024								
B118	040824WD0043	1.640	71.8*	73.7	58.9*	3.1	Sep-18	Sep-26	Volker Stevin Hwy 3:02 Pincher Greek, AB
		Tolerance Limits							
2023	17251B	1.663	82	75.7	62.8	2.5			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8				
Lower Limit		1.613	77	73.7	60.8				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ 1-Oct-24
DATE
Reviewed By: _____

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335

Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Limited
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Formulation:		Supplier: OZARK							
White WB 17251B		Tests Required							
Lab Sample Number	Batch Number 2024	Relative Density	Viscosity	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes) (Minutes)	Date Sampled 2024	Date Received 2024	Applicator and Location
		(25/25°C)	(Krebs)						
B120	050224WM0092	1.587*	78.2	75.5	61.7	3.2	June	Sep-27	EMCON Stettler, AB
B122	060724WD0108	1.591*	78.2	76.5	60.5	3.2	Aug-21	Sep-27	EMCON Hwy 884:10
		Tolerance Limits							
2023	17251B	1.663	82	75.7	62.8	2.5			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8				
Lower Limit		1.613	77	73.7	60.8				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____

8-Oct-24**DATE**

Reviewed By: _____

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.