

Project No.: 16335

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Formulation:		Supplier: OZARK							
White WB 801182/17251B		Tests Required							
Lab Sample Number	Batch Number 2024	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled 2024	Date Received 2024	Applicator and Location
B11	378817	1.623	78.0	75.3	61.6	9.6	Jun-5	Jun-11	Emcon Hwy 63:04 Sampler Athur Kavulok 780-675-2780
		Tolerance Limits							
2023	801182/17251B	1.663	82	75.7	62.8	8.2			
Tolerance Limits				± 2%	± 2%				
		± 0.05	± 5	absolute	absolute				
Upper Limit		1.713	87	77.7	64.8	20 max.			
Lower Limit		1.613	77	73.7	60.8	N/A			

Test not Required by AT

PER: _____ 2-Jul-25
Reviewed By: _____ DATE

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Formulation:		Supplier: OZARK							
White WB 801182/17251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location
	2025	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2025	2025	
B27	382709	1.619	78.4	75.4	61.7	9.3	Jul-2	Jul-3	Lafrentz Hwy 56:16 Con#23732
B29	382708	1.623	77.4	76.1	61.5	9.3	Jun-23	Jul-4	Emcon Hwy 2:38/2:40 Sampler Athur Kavulok 780-675-2780
Tolerance Limits									
2023	801182/17251B	1.663	82	75.7	62.8	8.2			
Tolerance Limits				± 2%	± 2%				
		± 0.05	± 5	absolute	absolute				
Upper Limit		1.713	87	77.7	64.8	20 max.			
Lower Limit		1.613	77	73.7	60.8	N/A			

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ 14-Jul-25

DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 818-5351

Tel +1 (780) 818-5355

To: Alberta Transportation

Technical Standards Branch

2nd Floor, Twin Atria Building

4999 - 98 Ave

Edmonton, AB T6B 2X3

Formulation:		Supplier: OZARK							
White WB 801182/17251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location
	2025	(25/25°C)	(Krebs)	Content (%)	(%)	(Minutes) (Minutes)	2025	2025	
B33	360771	1.647	78.2	77.7	61.7	9.7	Jul-5	Jul-8	Volker Stevin Hwy 3:16
B39	378820	1.632	78.4	75.4	61.4	9.8	Jul-4	Jul-14	Emcon Hwy 21:24
Tolerance Limits									
2023	801182/17251B	1.663	82	75.7	62.8	8.2			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8	20 max.			
Lower Limit		1.613	77	73.7	60.8	N/A			

* Indicates result outside tolerance limits.



Test not Required by AT

PER:

22-Jul-25

DATE

Reviewed By:

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3


Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 818-5351
Tel +1 (780) 818-5355

Formulation:		Supplier: OZARK							
White WB 801182/17251B		Tests Required							
Lab Sample Number	Batch Number 2025	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled 2025	Date Received 2025	Applicator and Location
B45	364289	1.614	78.2	75.6	61.7	10.0	Jul-15	Jul-17	Lafrentz Hwy 53:12 Con#23732
Tolerance Limits									
2023	801182/17251B	1.663	82	75.7	62.8	8.2			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8	20 max.			
Lower Limit		1.613	77	73.7	60.8	N/A			

* Indicates result outside tolerance limits.



Test not Required by AT

PER:  28-Jul-25
DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.