

# TRAFFIC PAINT TEST REPORT

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
Technical Standards Branch  
2nd Floor, Twin Atria Building  
4999 - 98 Ave  
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc  
5671 - 70 Street  
Edmonton, AB  
Canada T6B 3P6  
Tel +1 (780) 436-2152  
Fax +1 (780) 377-3599  
Tel +1 (780) 436-2152  
Fax +1 (780) 377-3599

Formulation:		Supplier: <b>OZARK</b>							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location
	2025	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2025	2025	
<b>B12</b>	378864	1.637	80.8	77.3	61.6	8.5	Jun-5	Jun-11	Emcon Hwy 63:04 Sampler Athur Kavulok 780-675-2780
Tolerance Limits									
<b>2023</b>	<b>801185/27251B</b>	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ 2-Jul-25

DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
Engineering Interpretation or evaluation of the test results is provided only on written request.

# TRAFFIC PAINT TEST REPORT

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
Technical Standards Branch  
2nd Floor, Twin Atria Building  
4999 - 98 Ave  
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc  
5671 - 70 Street  
Edmonton, AB  
Canada T6B 3P6  
Tel +1 (780) 436-2152  
Fax +1 (780) 377-3599  
  
Tel +1 (780) 436-2152  
Fax +1 (780) 377-3599

Formulation:		Supplier: OZARK							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location
	2025	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2025	2025	
B28	364303	1.620	77.2	76.8	61.5	8.9	Jul-2	Jul-3	Lafrentz Hwy 56:16 Con#23732
B30	364282	1.630	82.3	77.3	62.2	8.6	Jun-23	Jul-4	Emcon Hwy 2:38/2:40 Sampler Athur Kavulok 780-675-2780
Tolerance Limits									
2023	801185/27251B	1.652	82.5	76.3	60.8	8.3			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ 14-Jul-25  
DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16450


 Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

Formulation:		Supplier: <b>OZARK</b>							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location
	<b>2025</b>						2025	2025	
<b>B34</b>	378866	1.647	80.1	77.1	61.9	8.5	Jul-5	Jul-8	Volker Stevin Hwy 3:16
<b>B40</b>	379696	1.636	79.1	77.0	61.7	8.9	Jul-4	Jul-14	Emcon Hwy 21:24
Tolerance Limits									
<b>2023</b>	<b>801185/27251B</b>	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ 22-Jul-25

DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

# TRAFFIC PAINT TEST REPORT

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
Technical Standards Branch  
2nd Floor, Twin Atria Building  
4999 - 98 Ave  
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc  
5671 - 70 Street  
Edmonton, AB  
Canada T6B 3P6  
Tel +1 (780) 818-5351  
Tel +1 (780) 818-5355

Formulation:		Supplier: OZARK							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location
B46	2025 397938	1.613	78.2	77.3	61.9	9.1	Jul-15	Jul-17	Lafrentz Hwy 53:12 Con#23732
Tolerance Limits									
2023	801185/27251B	1.652	82.5	76.3	60.8	8.3			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ 28-Jul-25  
DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
Engineering Interpretation or evaluation of the test results is provided only on written request.