Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions

5671 - 70 Street Edmonton, AB Canada T6B 3P6

Tel +1 (780) 436-2152 Fax +1 (780) 377-3599

Tel +1 (780) 436-2152 Fax +1 (780) 377-3599

Formulation:		Supplier:			OZARK	•			
Whit	White WB 17251		Tests R	equired					
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample	Number	Density		Volatile	Content	Touch	Sampled	Received	THE PROPERTY AND A SECOND SECO
Number	2021	(25/25°C)	(Krebs)	Content (%)	(%)	(Minutes)	2021	2021	
B112	031221WM0069	1.573*	78.2	78.8	60.1	3.1	Aug-26	Sep-13	Volker Stevin Lethbridge, AB
			Toleranc	e Limits					
2020	17251	1.643	84.3	76.7	61.6				
Tole	Tolerance Limits			± 2%	± 2%				
		± 0.05	± 5	absolute	absolute				
U	Upper Limit		89.3	78.7	63.6				
L.	Lower Limit		79.6	74.3	59.6				

* Indicates result outside tolerance limits.

Test not Required by AT

PER:

Reviewed By:

Reporting of these results constitutes a testing service only.

Engineering Interpretation or evaluation of the test results is provided only on written request.

Project No.: 16335

wood.

Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building

4999 - 98 Ave Edmonton, AB T6B 2X3 Distribution Addressee: Wood Environment & Infrastructure Solutions

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Tel +1 (780) 436-2152 Fax +1 (780) 377-3599

Formulation: White WB 17251		Supplier:			OZARK				
			Tests Re	equired					
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample	Number	Density		Volatile	Content	Touch	Sampled	Received	
Number				Content					
	2021	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2021	2021	
B143	032621WM0107	1.632	77.8*	76.9	61.2	3.1	Oct-17	Oct-18	Volker Stevin Hwy 4: 12 CMA24
B147	032621WM0105	1.661	79.0	73.9*	62.3	3.0	Oct-2	Oct-18	Volker Stevin Hwy 529 : 04/06 , 526 : 06 875 : 02 CMA24
			Toleranc	e Limits					
2020	17251	1.643	84.3	76.7	61.6				
Tolerance Limits				± 2%	± 2%				
		± 0.05	± 5	absolute	absolute				
Upper Limit		1.693	89.3	78.7	63.6				
Lower Limit		1.593	79.6	74.3	59.6				
						*	la dia aka a		ide televenee limite

Indicates result outside tolerance limits.

Test not Required by AT

PER:

3-Nov-21 DATE

Reviewed By:

Reporting of these results constitutes a testing service only.

Engineering Interpretation or evaluation of the test results is provided only on written request.

Project No.: 16335

wood.

Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Tel +1 (780) 436-2152 Fax +1 (780) 377-3599

Formulation:		Supplier:		OZARK					
White WB 17251		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample	Number	Density		Volatile	Content	Touch	Sampled	Received	
Number				Content					
	2021	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2021	2021	
B149	032521WM0101	1.610	78.2*	75.5	62.1	2.9	Oct-3	Oct-13	Volker Stevin Hwy 36 : 02 and 36 : 06 CMA24
B159	032521WM0103	1.618	78.6*	76.2	62.6	2.9	Oct-18	Oct-21	Volker Stevin Hwy 4: 02 CMA24
		Tolerance Limits					NaZ		
2020	17251	1.643	84.3	76.7	61.6				
Tolerance Limits				± 2%	± 2%				
		± 0.05	± 5	absolute	absolute				
Upper Limit		1.693	89.3	78.7	63.6				
Lower Limit		1.593	79.6	74.3	59.6				
							Indianta.		de televenes limite

* Indicates result outside tolerance limits.

Test not Required by AT

PER:

15-Nov-25 DATE

Reviewed By:

Reporting of these results constitutes a testing service only.

Engineering Interpretation or evaluation of the test results is provided only on written request.

Project No.: 16335

wood.

Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Tel +1 (780) 436-2152 Fax +1 (780) 377-3599

Formulation: White WB 17251		Supplier:			OZARK				
			Tests R	equired					
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample	Number	Density		Volatile	Content	Touch	Sampled	Received	
Number				Content					
	2021	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2021	2021	
B172	031221WM0069	1.662	80.6	77.1	63.5	3.0	Nov-3	Nov-10	Hwy 680 : 02
			Toleranc	e l imite)		
2020	17251	1.643	84.3	76.7	61.6				
Tole	Tolerance Limits			± 2%	± 2%				
		± 0.05	±5	absolute	absolute				
Upper Limit		1.693	89.3	78.7	63.6				
Lower Limit		1.593	79.6	74.3	59.6				

* Indicates result outside tolerance limits.	13. 10
Test not Required by AT	
PER:	13-Dec-21
	DATE
Reviewed By:	

Reporting of these results constitutes a testing service only.

Engineering Interpretation or evaluation of the test results is provided only on written request.