

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: Wood Environment & Infrastructure Solutions

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: OZARK							
Yellow WB 27251		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Touch	Date Sampled	Date Received	Applicator and Location
	2022	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2022	2022	
B14	031022YM0091	1.678	82.7	77.4	62	2.8	Jun-2	Jun-13	Volker Stevin Fort Macleod
Tolerance Limits									
2020	27251	1.673	82.3	77.8	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

***Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects**

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **21-Jun-22**
 DATE
 Reviewed By:  _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: Wood Environment & Infrastructure Solutions

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B18	110921YM0454	1.567*	79.3	76.2	60.8	3.1	Jun-30	Jul-5	ACP Con# 21920 Hwy 16: 24
Tolerance Limits									
2020	27251	1.631	77.6	77.0	60.4				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.681	87.6	79.0	62.4				
Lower Limit		1.581	77.6	75.0	58.4				

***Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects**

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **18-Jul-22**
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: Wood Environment & Infrastructure Solutions

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B22	030222YM0059	1.643	81.2	77.4	61.8	2.8	Jun-22	Jul-6	Volker Stevin Carston
Tolerance Limits									
2021	27251	1.673	82.3	77.8	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

***Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects**

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **21-Jun-22**
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: Wood Environment & Infrastructure Solutions

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B36	032521YM0102	1.577*	79.3	78.6	63.1	3.3	Jul-14	N/A	AAA Striping Hwy 680 : 02
Tolerance Limits									
2021	27251	1.673	82.3	77.8	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

***Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects**

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **26-Jul-22**
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: Wood Environment & Infrastructure Solutions

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599


To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
Tests Required									
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled 2022	Date Received 2022	Applicator and Location
B38	030322YM0061	1.643	81.5	77.6	62.1	3.3	Jun-27	Jul-18	Volker Stevin Hwy 6, 04/ 61, 06/ 839 :04 / 839: 12 Foremost, AB CMA24
Tolerance Limits									
2021	27251	1.673	82.3	77.8	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

***Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects**

* Indicates result outside tolerance limits.
 Test not Required by AT

PER: _____  **15-Aug-22**
 DATE
 Reviewed By: _____ 

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: Wood Environment & Infrastructure Solutions

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B52	050422YM0185	1.732*	96.2*	80.7	63.1	3.1	Jul-28	Jul-29	Lafrentz Hwy 15: 03/04
		Tolerance Limits							
2021	27251	1.673	82.3	77.8	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

*Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **23-Aug-22**
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: Wood Environment & Infrastructure Solutions

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B54	110821YM0448	1.600	79.3	76.4	61.1	3.3	Aug-3	Aug-5	Hwy 845 : 02 Con# 19871
Tolerance Limits									
2020	27251	1.631	77.6	77.0	60.4				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.681	87.6	79.0	62.4				
Lower Limit		1.581	77.6	75.0	58.4				

***Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects**

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **30-Aug-22**
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: Wood Environment & Infrastructure Solutions

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B56	052322YM0233	1.625	80.3	77.6	62.2	3.4	Aug-10	Aug-11	Volker Stevin Hwy 36: 02 Taber, AB
Tolerance Limits									
2021	27251	1.673	82.3	77.8	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

***Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects**

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ 30-Aug-22

Reviewed By: _____ DATE

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: Wood Environment & Infrastructure Solutions

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled 2022	Date Received 2022	Applicator and Location
B68	051922YM0212	1.611	78.2	77.1	61.7	3.2	Aug-25	Aug-30	Emcon Hwy 28: 10 Km 14; CMA7 Sampler Athur Kavulok 780-675-2780
B74	052022YM0216	1.625	83.0	77.0	61.8	3.2	Aug-24	Aug-30	Taber , AB CMA 24
Tolerance Limits									
2021	27251	1.673	82.3	77.8	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

***Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects**

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **12-Sep-22**

DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: Wood Environment & Infrastructure Solutions

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled 2022	Date Received 2022	Applicator and Location
B70	110421YM0444	1.651	81.8	77.2	61.6	3.1	Aug-26	Aug-30	Emcon Hwy 881 : 10 Km 11 : 09
B76	110221YM0436	1.610	75.0*	75.7	60.5	2.5	Aug-26	Sep-2	Emcon Hwy 27:08 east of Hwy 21 Hanna Alberta.,
Tolerance Limits									
2020	27251	1.631	77.6	77.0	60.4				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.681	87.6	79.0	62.4				
Lower Limit		1.581	77.6	75.0	58.4				

*Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects

* Indicates result outside tolerance limits.
 Test not Required by AT

PER: **12-Sep-22**
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: Wood Environment & Infrastructure Solutions

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B84	052322YM0232	1.624	80.1	77.0	61.7	3.0	Sep-8	Sep-8	Emcon Vermilion Sampler Dipesh Pokhrel 780-581-5172
Tolerance Limits									
2021	27251	1.673	82.3	77.8	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

***Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects**

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **19-Sep-22**
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 15335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP E&I Canada Limited

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B86	050422YM0185	1.624	82.5	77.8	62.4	3.3	Aug-24	Sep-9	Lafrentz Hwy 2A : 12
Tolerance Limits									
2021	27251	1.673	82.3	77.8	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

***Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects**

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **26-Sep-22**

Reviewed By: _____

 DATE

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP E&I Canada Limited


To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled 2022	Date Received 2022	Applicator and Location
B94	110221YM0438	1.588	75.8	76.2	60.9	3.1	Sep-9	Sep-16	Emcon Drumheller Wo#021-1495 Hwy 837
B96	110221YM0436	1.644	79.6	77.0	61.8	3.1	Sep-14	Sep-16	Emcon Hwy 855 : 04
Tolerance Limits									
2020	27251	1.631	77.6	77.0	60.4				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.681	87.6	79.0	62.4				
Lower Limit		1.581	77.6	75.0	58.4				

***Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects**

* Indicates result outside tolerance limits.

 Test not Required by AT

PER: _____  _____ **26-Sep-22**
 DATE
 Reviewed By: _____  _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP E&I Canada Limited

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled 2022	Date Received 2022	Applicator and Location
B98	052022YM0214	1.625	84.0	77.8	62.6	3.4	Sep-15	Sep-20	Volker Stevin Lethbridge CMA 25
Tolerance Limits									
2021	27251	1.673	82.3	77.8	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

***Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects**

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **6-Oct-22**

DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP E&I Canada Limited

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled 2022	Date Received 2022	Applicator and Location
B106	011722YM0008	1.638	80.8	76.3	61.0	3.3	Sep-28	Oct-3	Volker Stevin Hwy 549:04
B108	072722YM0320	1.609*	79.3	77.3	61.9	3.2	Oct-3	Oct-4	Lafrentz Hwy 88:12 CMA 2 Sampler Jesse Kasour 780-618-1685
Tolerance Limits									
2021	27251	1.673	82.3	77.8	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

*Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ 17-Oct-22

DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16450




Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP E&I Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B116	110921YM0452	1.607	79.3	76.6	61.3	3.3	Sep-13	Oct-7	Lafrentz Hwy 2:48/2:50 CMA 6 West Sampler by: Thomas Willier / Russell Romick
Tolerance Limits									
2020	27251	1.631	77.6	77.0	60.4				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.681	87.6	79.0	62.4				
Lower Limit		1.581	77.6	75.0	58.4				

***Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects**

* Indicates result outside tolerance limits.
 Test not Required by AT

PER: _____ **24-Oct-22**
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP E&I Canada Limited

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B122	040422YM0136	1.645	80.4	77.5	62.2	3.1	Oct-14	Oct-18	Emcon Hwy 18:10 Km 49:96 CMA10 Sampler by: Athur Kavulok 780-675-2780
		Tolerance Limits							
2021	27251	1.673	82.3	77.8	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

***Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects**

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **24-Oct-22**
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP E&I Canada Limited

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3


Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled 2022	Date Received 2022	Applicator and Location
	2022								
B128	072722YM0322	1.612*	76.8*	77.0	61.4	3.0	Oct-5	Oct-21	Lafrentz Hwy 47 : 06 Con#22686 Sampler by Ali Joyo 403-369-3499
B130	072722YM0320	1.577*	79.0	77.1	61.7	3.2	Oct-14	Oct-24	Lafrentz Hwy 986 : 02 CMA 2 Sampler by Jesse Kasouf 780-618-1685
B132	071822YM0303	1.612*	77.4	77.6	62.1	3.2	Sep-26	Oct-24	Lafrentz Hwy 60
Tolerance Limits									
2021	27251	1.673	82.3	77.8	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

*Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects

* Indicates result outside tolerance limits.

 Test not Required by AT

PER: _____ **31-Oct-22**
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP E&I Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Formulation: Yellow WB 27251		Supplier: OZARK							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B144	052422YM0234	1.625	81.8	77.8	62.2	3.1	Oct-17	Nov-4	Lafrentz Hwy 49 -2A Intersection
2021 27251		1.673	82.3	77.8	62.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.723	87.3	79.8	64.2				
Lower Limit		1.623	77.3	75.8	60.2				

*Note: Formulation numbers do not match any current approved traffic paints for use on Alberta Transportation Projects

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **22-Nov-22**
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.