TRAFFIC PAINT TEST REPORT

Project No.: 16335

wood.

Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: Wood Environment & Infrastructure Solutions

5671 - 70 Street

Edmonton, AB

Canada T6B 3P6

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Tel +1 (780) 436-2152

Fax +1 (780) 377-3599

Formulation:		Supplier:		OZARK					
White WB 14251			Tests Re	equired					
Lab	Batch	Relative	Viscosity	Non-	Pigment	Date	Date	Date	Applicator and Location
Sample	Number	Density		Volatile	Content	Sampled	Received	Reported	
Number				Content					
	2020	(25/25°C)	(Krebs)	(%)	(%)	2020	2020	2020	
B136	062520WM0255	1.638	84.0	80.0	80.0	Sep-14	Sep-18	Sep-29	Lafrentz Hwy 658 ; 02
B144	062520WM0255	1.554*	74.4*	79.6	61.3	Sep-18	Sep-24	Sep-29	Lafrentz Hwy 579:02
			Toleranc	e Limits					
2019	14251	1.687	82.1	78.5	61.8				
Tolerance Limits				± 2%	± 2%				
		± 0.05	± 5	absolute	absolute				
Upper Limit		1.737	87.1	80.5	63.8				
Lower Limit		1.637	77.1	76.5	59.8				
	·	·				*	Indicates	rocult oute	ide tolerance limits

* Indicates result outside tolerance limits.

Test not Required by AT

PER:

29-Sep-19 DATE

Reviewed By:

Reporting of these results constitutes a testing service only.

Engineering Interpretation or evaluation of the test results is provided only on written request.