

TRAFFIC PAINT TEST REPORT

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.



To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: PMI								
White WB 10-3040		Tests Required								
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location	
B50	BKF003260002	1.563	80.1	73.7	58.2	2.9	Jul-13	Jul-14	Main Roads Hwy 2:24 & 26	
Tolerance Limits										
2020	White 10-3040	1.585	85	74.1	57.8					
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute					
Upper Limit		1.635	90	76.1	59.8					
Lower Limit		1.535	80	72.1	55.8					

Note: Yellow Paint Formulation 70291 - , batch number - W20C5228, did not match submitted manufacturer's samples.

* Indicates result outside tolerance limits.
 Test not Required by AT

PER:  Jul-27
 DATE
 Reviewed By: 

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.