

TRAFFIC PAINT TEST REPORT

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Formulation:		Supplier: PMI							
White WB 10-3008		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic	Date Sampled	Date Received	Applicator and Location
	2025						2025	2025	
B61	BOFM0011149001	1.558	79.1	74.7	58.2	7.5	Jul-18	Aug-7	Line King Hwy 19:10 Con#24948
B63	BOGM0011192005	1.545*	77.6	74.3	57.8	7.8	Aug-6	Aug-12	AECON Hwy 40:10 Con#24629
Tolerance Limits									
2024	White 10-3008	1.607	79.4	74.6	58.0	7.2			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.657	84.4	76.1	59.8	20 max.			
Lower Limit		1.557	74.4	72.1	55.8	N/A			

* Indicates result outside tolerance limits.



Test not Required by AT

PER:

Aug-26
DATE

Reviewed By:

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

Project No.: EA16450

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Formulation:		Supplier:		PMI					
White WB 10-3008		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location
	2025	(25/25°C)	(Krebs)	Content (%)	(%)		2025	2025	
B77	BOGM0011192005	1.558	82.2	74.6	58.6	7.5	Aug-14	Aug-18	Line King Hwy 201:08 Con#23855
		Tolerance Limits							
2024	White 10-3008	1.607	79.4	74.6	58.0	7.2			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.657	84.4	76.1	59.8	20 max.			
Lower Limit		1.557	74.4	72.1	55.8	N/A			

* Indicates result outside tolerance limits.



Test not Required by AT

PER:

Aug-26
DATE

Reviewed By:

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Formulation:		Supplier: PMI							
White WB 10-3008		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location
	2025	(25/25°C)	(Krebs)	(%)	(%)		2025	2025	
B97	BOGM0011192005	1.574	82.2	74.8	58.5	Jan-7	Aug-23	Sep-2	Line King Hwy 765:02 Cont#24948
Tolerance Limits									
2024	White 10-3008	1.607	79.4	74.6	58.0	7.2			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.657	84.4	76.1	59.8	20 max.			
Lower Limit		1.557	74.4	72.1	55.8	N/A			

* Indicates result outside tolerance limits.

Test not Required by AT

PER: Sep-15
DATE

Reviewed By:

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.