

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16335




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3


Distribution Addressee: WSP E&I Canada Limited  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
White WB 985221		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
<b>B13</b>	CPP2305W0507	1.659	88.0	80.2	63.2	3.6	May-23	May-24	Lafrantz Hwy 5.03 & Hwy 28A Con#15188
<b>Tolerance Limits</b>									
	<b>985221</b>								
Tolerance Limits									
Upper Limit									
Lower Limit									

\* Indicates result outside tolerance limits.

 Test not Required by AT

Note: White Paint Formulation is not on Alberta Transportations approved list.

PER:  6-Jun-22  
 DATE  
 Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.



**TRAFFIC PAINT TEST REPORT**

Project No.: EA16335



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation: White WB 985221		Supplier: PPG							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled 2023	Date Received 2023	Applicator and Location
<b>B42</b>	CPP2305W0507	1.639	87.2	79.4	62.5	3.4	Jun-26	Jul-3	Lafrentz Hwy 22:30 7& Hwy 16:04 Con#22686
<b>B44</b>	CPP2305W0507	1.609	81.0	77.9	61.5	3.2	Jun-30	Jul-3	Lafrentz Hwy 16:04 Con#22686
<b>Tolerance Limits</b>									
	<b>985221</b>								
Tolerance Limits									
Upper Limit									
Lower Limit									

\* Indicates result outside tolerance limits.



Test not Required by AT

Note: White Paint Formulation is not on Alberta Transportations approved list.

PER: \_\_\_\_\_ 17-Jul-23  
 DATE  
 Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16335



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
White WB 985221		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Touch	Date Sampled	Date Received	Applicator and Location
	2023	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2023	2023	
<b>B74</b>	CPP2305W0507	1.600	76.8	76.5	60.3	3.3	Jul-14	Jul-25	Lafrentz Hwy 16:04 Con#22686
<b>B75</b>	CPP2305W0507	1.675	93.4*	80.4	63.3	3.4	Jul-24	Jul-25	Lafrentz Hwy 47:06 & Hwy 16:06 Con#22686
<b>Tolerance Limits</b>									
	<b>985221</b>								
Tolerance Limits									
Upper Limit									
Lower Limit									

\* Indicates result outside tolerance limits.



Test not Required by AT

**Note: White Paint Formulation is not on Alberta Transportations approved list.**

PER: \_\_\_\_\_ **8-Aug-23**  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16335




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

<b>Formulation:</b>		<b>Supplier: PPG</b>							
<b>White WB 985221</b>		<b>Tests Required</b>							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
<b>B130</b>	CPP2305W0507	1.683	96.0*	82.2	60.9	3.5	Sep-13	Sep-18	Lafrentz Hwy 2AKm 0+000 to Hwy 679 Km 20+807 Con#22265
<b>Tolerance Limits</b>									
<b>985221</b>									
Tolerance Limits									
Upper Limit									
Lower Limit									

\* Indicates result outside tolerance limits.

 Test not Required by AT

**Note: White Paint Formulation is not on Alberta Transportations approved list.**

PER: \_\_\_\_\_ **25-Sep-23**

Reviewed By: \_\_\_\_\_ DATE

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

