

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
White Acetone 986061		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density		Volatile Content	Content	Traffic	Sampled	Received	
	2025	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2025	2025	
B3	CPP2410W1049	1.730	84.7	74.7	56.8	8.9	May-28	May-29	Lafrentz Hwy4, 28:02 and 37:04 Con#17549
Tolerance Limits									
	986061	N/A	N/A	N/A	N/A	N/A			
Tolerance Limits			± 5	± 2% absolute	± 2% absolute				
Upper Limit			90	76.0	57.5				
Lower Limit		1.35	75	71.0	52.0				

*Note:

* Indicates result outside tolerance limits.



Test not Required by AT

PER

18-Jun-25

DATE

Reviewed By:

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
White Acetone 986061		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density		Volatile Content	Content	Traffic	Sampled	Received	
	2025	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2025	2025	
B21	CPP2504W0182	1.481	88.6	76.7	58.6	9.1	Jun-11	Jun-19	Alberta Transportation Hwy 33:12
B23	CPP2504W0217	1.489	85.1	76.1	59.0	9.2	Jun-17	Jun-19	Lafrentz Hwy 64 to 14Km N of Hwy 49 Km 0.000 to Km 19.400 Con#24596
B25	CPP2504W0182	1.493	93.5*	76.2	87.7	9.6	May-4	Jun-26	Lafrentz Hwy 2:50
Tolerance Limits									
	986061	N/A	N/A	N/A	N/A	N/A			
Tolerance Limits			± 5	± 2% absolute	± 2% absolute				
Upper Limit			90	76.0	57.5	20 max.			
Lower Limit		1.35	75	71.0	52.0	N/A			

*Note:

* Indicates result outside tolerance limits.



Test not Required by AT

PER

14-Jul-25

DATE

Reviewed By:

Reporting of these results constitutes a testing service only.

Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 818-5351
Tel +1 (780) 818-5355

Formulation:		Supplier: PPG							
White Acetone 986061		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density		Volatile Content	Content	Traffic	Sampled	Received	
	2025	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2025	2025	
B31	CPP2504W0286	1.487	86.1	75.7	58.2	9.5	Jul-2	Jul-8	No Applicator and Location this from AT Calgray office under name of Susang Patel
Tolerance Limits									
986061		N/A	N/A	N/A	N/A	N/A			
Tolerance Limits			± 5	± 2% absolute	± 2% absolute				
Upper Limit			90	76.0	57.5	20 max.			
Lower Limit		1.35	75	71.0	52.0	N/A			

*Note:

* Indicates result outside tolerance limits.



Test not Required by AT

PER

22-Jul-25

DATE

Reviewed By:

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.