

TRAFFIC PAINT TEST REPORT

Project No.: EA16450

WSP

Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

| Formulation: | | Supplier: PPG | | | | | | | |
|-----------------------|--------------|------------------|-----------|----------------------|-----------------|----------------|--------------|---------------|--|
| Yellow Acetone 986063 | | Tests Required | | | | | | | |
| Lab Sample Number | Batch Number | Relative Density | Viscosity | Non-Volatile Content | Pigment Content | Dry to Traffic | Date Sampled | Date Received | Applicator and Location |
| | 2025 | (25/25°C) | (Krebs) | (%) | (%) | (Minutes) | 2025 | 2025 | |
| B4 | CPP2410Y1060 | 1.417 | 80.8 | 74.8 | 53.0 | 8.5 | May-28 | May-28 | Lafrentz Hwy4, 28:02 and 37:04 Con#17549 |
| Tolerance Limits | | | | | | | | | |
| | 986063 | N/A | N/A | N/A | N/A | N/A | | | |
| Tolerance Limits | | | | ± 2% absolute | ± 2% absolute | | | | |
| Upper Limit | | 1.45 | 90 | 75.0 | 55.0 | | | | |
| Lower Limit | | 1.32 | 75 | 70.0 | 49.0 | | | | |

*Note:

* Indicates result outside tolerance limits.



Test not Required by AT

PER:

18-Jun-25

DATE

Reviewed By:

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

| Formulation: | | Supplier: PPG | | | | | | | |
|-----------------------|--------------|-------------------------------|----------------------|-----------------------------|------------------------|-----------------------------|----------------------|-----------------------|---|
| Yellow Acetone 986063 | | Tests Required | | | | | | | |
| Lab Sample Number | Batch Number | Relative Density (25/25°C) | Viscosity (Krebs) | Non-Volatile Content (%) | Pigment Content (%) | Dry to Traffic (Minutes) | Date Sampled 2025 | Date Received 2025 | Applicator and Location |
| B22 | CPP2503Y0134 | 1.446 | 88.8 | 76.0 | 55.2 | 8.7 | Jun-11 | Jun-19 | Alberta Transportation Hwy 33:12 |
| B24 | CPP2503Y0134 | 1.433 | 83.2 | 75.6 | 54.4 | 8.3 | Jun-17 | Jun-19 | Lafrentz Hwy 64 to 14Km N of Hwy 49 Km 0.000 to Km 19.400 Con#24596 |
| B26 | CPP2504Y0221 | 1.427 | 82.0 | 75.1 | 54.8 | 8.3 | May-4 | Jun-26 | Lafrentz Hwy 2:50 |
| Tolerance Limits | | | | | | | | | |
| 986063 | | N/A | N/A | N/A | N/A | N/A | | | |
| Tolerance Limits | | | | ± 2% absolute | ± 2% absolute | | | | |
| Upper Limit | | 1.45 | 90 | 75.0 | 55.0 | 20 max. | | | |
| Lower Limit | | 1.32 | 75 | 70.0 | 49.0 | N/A | | | |

*Note:

* Indicates result outside tolerance limits.



Test not Required by AT

PER:

14-Jul-25

DATE

Reviewed By:

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 818-5351
Tel +1 (780) 818-5355

| | | | | | | | | | |
|------------------------------|---------------|-----------------------|------------|----------------------|-----------------|----------------|--------------|---------------|---|
| Formulation: | | Supplier: PPG | | | | | | | |
| Yellow Acetone 986063 | | Tests Required | | | | | | | |
| Lab Sample Number | Batch Number | Relative Density | Viscosity | Non-Volatile Content | Pigment Content | Dry to Traffic | Date Sampled | Date Received | Applicator and Location |
| | 2025 | (25/25°C) | (Krebs) | (%) | (%) | (Minutes) | 2025 | 2025 | |
| B32 | CPP2504Y0222 | 1.393 | 71.8* | 73.9 | 52.2 | 8.7 | Jul-2 | Jul-8 | No Applicator and Location this from AT Calgray office under name of Susang Patel |
| Tolerance Limits | | | | | | | | | |
| | 986063 | N/A | N/A | N/A | N/A | N/A | | | |
| Tolerance Limits | | | | ± 2% absolute | ± 2% absolute | | | | |
| Upper Limit | | 1.45 | 90 | 75.0 | 55.0 | 20 max. | | | |
| Lower Limit | | 1.32 | 75 | 70.0 | 49.0 | N/A | | | |

*Note:

* Indicates result outside tolerance limits.



Test not Required by AT

PER:  **22-Jul-25**
DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.