

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
White WB EF-61-0124		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Touch	Date Sampled	Date Received	Applicator and Location
	2023	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2023	2023	
<b>B3</b>	CPP230W0349	1.594	77.6	77.7	59.6	2.7	May-16	May-17	Alberta Transportation Edson Hwy16 EB @ JG Sampler D. Farr 780-712-3372
<b>Tolerance Limits</b>									
<b>2022</b>	<b>EF-61-0124</b>	<b>1.612</b>	<b>81.7</b>	<b>77.7</b>	<b>59.1</b>				
Tolerance Limits		± 0.05	± 5	± 2%	± 2%				
			absolute	absolute					
Upper Limit		1.662	86.7	79.7	61.1				
Lower Limit		1.562	76.7	75.7	57.1				

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ 23-May-23

Reviewed By: \_\_\_\_\_ DATE

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
White WB EF-61-0124		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
<b>B7</b>	CPP2304W0381	1.603	80.0	77.6	59.5	2.5	May-18	May-23	Volker Stevin Hwy 36: 04 Taber, AB
<b>Tolerance Limits</b>									
<b>2021</b>	<b>EF-61-0124</b>	<b>1.612</b>	<b>81.7</b>	<b>77.7</b>	<b>59.1</b>				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.662	86.7	79.7	61.1				
Lower Limit		1.562	76.7	75.7	57.1				

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ **30-May-23**  
 DATE  
 Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
White WB EF-61-0124		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Touch	Date Sampled	Date Received	Applicator and Location
	2023	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2023	2023	
<b>B19</b>	CPP2304W0397	1.615	80.1	77.6	59.6	2.6	May-28	Jun-5	Volker Stevin Hwy 879:04 foremost CMA24
<b>B24</b>	CPP2303W0294	1.578	76.7	77.2	59.4	2.4	May-24	Jun-8	Ledcor Hwy 43:14 CMA23
<b>Tolerance Limits</b>									
<b>2021</b>	<b>EF-61-0124</b>	<b>1.612</b>	<b>81.7</b>	<b>77.7</b>	<b>59.1</b>				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.662	86.7	79.7	61.1				
Lower Limit		1.562	76.7	75.7	57.1				

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ 20-Jun-23  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

<b>Formulation:</b>		<b>Supplier: PPG</b>							
<b>White WB EF-61-0124</b>		<b>Tests Required</b>							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
<b>B82</b>	CPP2303W0294	1.633	79.3	77.9	59.5	2.6	Aug-1	Aug-2	Ledcor Hwy 751:02 CN Sampler D, Farr 780-712-3372
<b>Tolerance Limits</b>									
<b>2021</b>	<b>EF-61-0124</b>	<b>1.612</b>	<b>81.7</b>	<b>77.7</b>	<b>59.1</b>				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.662	86.7	79.7	61.1				
Lower Limit		1.562	76.7	75.7	57.1				

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **15-Aug-23**  
 DATE  
 Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.