

TRAFFIC PAINT TEST REPORT

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
White WB EF-61-0139		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location
B1	2025 CPP2504W0298	1.621	74.6*	78.2	60.8	8.6	May-16	May-23	Hwy 39:10 and Hwy795:06 Con#19883
Tolerance Limits									
2023	EF-61-0139	1.621	80.4	78.7	59.7	8.8			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute	20 max.			
Upper Limit		1.671	85.4	80.7	61.7	20 max.			
Lower Limit		1.571	75.4	76.7	57.7	N/A			

* Indicates result outside tolerance limits.

 Test not Required by AT

PER: _____ 3-Jun-25

DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.