

# TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
Technical Standards Branch  
2nd Floor, Twin Atria Building  
4999 - 98 Ave  
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc  
5671 - 70 Street  
Edmonton, AB  
Canada T6B 3P6  
Tel +1 (780) 818-5351  
Tel+1 (780) 818-5355

Formulation:		Supplier: PPG							
White WB EF-61-0140		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
	2025						2025	2025	
B41	CPP2503W0180	1.600*	75.6	78.2	60.9	10.5	Jul-9	Jul-14	Line West Deerfoot improvement Median Widening 32 Ave to Beddington Trail Con#23534
Tolerance Limits									
2023	EF-61-0140	1.681	78	79	62.2	8.2			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute	20 max.			
Upper Limit		1.731	83	81.0	64.2	20 max.			
Lower Limit		1.631	73	77.0	60.2	N/A			

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ 22-Jul-25

DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
Engineering Interpretation or evaluation of the test results is provided only on written request.