

TRAFFIC PAINT TEST REPORT

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
Yellow WB EF-62-0124		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B4	CPP2303Y0295	1.522	76.4*	76.2	54.8	2.6	May-16	May-17	Alberta Transportation Edson Hwy16 EB @ JG Sampler D. Farr 780-712-3372
Tolerance Limits									
2022	EF-62-0124	1.532	83.5	76.9	55.1				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.582	88.5	78.9	57.1				
Lower Limit		1.482	78.5	74.9	53.1				

* Indicates result outside tolerance limits.
 Test not Required by AT

PER:  **23-May-23**
 DATE
 Reviewed By: 

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
Yellow WB EF-62-0124		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B8	CPP2303Y0350	1.509	77.4	76.3	55.1	2.4	May-23	May-18	Volker Stevin Hwy 36: 04 Taber, AB
Tolerance Limits									
2021	EF-62-0124	1.532	83.5	76.9	55.1				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.582	88.5	78.9	57.1				
Lower Limit		1.482	78.5	74.9	53.1				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **30-May-23**
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
Yellow WB EF-62-0124		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled 2023	Date Received 2023	Applicator and Location
B25	CPP2303Y0296	1.538	76.0*	76.2	54.8	2.4	May-24	Jun-8	Ledcor Hwy 43:14 CMA23
Tolerance Limits									
2021	EF-62-0124	1.532	83.5	76.9	55.1				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.582	88.5	78.9	57.1				
Lower Limit		1.482	78.5	74.9	53.1				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____

20-Jun-23
DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB EF-62-0124		Supplier: PPG							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B83	CPP2303Y0295	1.535	77.4*	76.6	55.2	2.4	Aug-1	Aug-2	Ledcor Hwy 751:02 CN Sampler D. Farr 780-712-3372
Tolerance Limits									
2021	EF-62-0124	1.532	83.5	76.9	55.1				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.582	88.5	78.9	57.1				
Lower Limit		1.482	78.5	74.9	53.1				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ 15-Aug-23

Reviewed By: _____ DATE

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
Yellow WB EF-62-0124		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
B117	CPP2306Y0646	1.511	77*	76.7	54.9	2.7	Aug-26	Sep-5	Volker Stevin Carston Hwy 877:06 Taber, AB CMA24
Tolerance Limits									
2021	EF-62-0124	1.532	83.5	76.9	55.1				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.582	88.5	78.9	57.1				
Lower Limit		1.482	78.5	74.9	53.1				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **18-Sep-23**
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP E&I Canada Limited
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
Yellow WB EF-62-0124		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch (Minutes)	Date Sampled	Date Received	Applicator and Location
	2023						2023	2023	
B149	CPP2306Y0706	1.450*	73.4*	75.1	56.0	3.1	Sep-21	Sep-21	Emcon Hwy 803 North of Hwy 28 Sampler Ryan Lvider 780-6442822
B157	CPP2306Y0646	1.521	76.0*	76.4	55.1	3.2	Sep-28	Sep-28	Emcon Hwy 779:02
Tolerance Limits									
2021	EF-62-0124	1.532	83.5	76.9	55.1				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.582	88.5	78.9	57.1				
Lower Limit		1.482	78.5	74.9	53.1				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ **10-Oct-23**
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.