

TRAFFIC PAINT TEST REPORT

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 818-5351
Tel +1 (780) 818-5355

Formulation:		Supplier: PPG							
Yellow WB EF-62-0140		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Touch	Date Sampled	Date Received	Applicator and Location
	2025	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2025	2025	
B42	CPP2503Y0181	1.530*	75.6	77.6	57.2*	10.2	Jul-9	Jul-14	Line West Deerfoot improvement Median Widening 32 Ave to Beddington Trail Con#23534
		Tolerance Limits							
2023	EF-62-0140	1.649	79	76.6	60.4	7.5			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute	20 max.			
Upper Limit		1.699	84	78.6	62.4	20 max.			
Lower Limit		1.599	74	74.6	58.4	N/A			

* Indicates result outside tolerance limits.

 Test not Required by AT

PER:  21-Jul-25

Reviewed By:  DATE

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.