

TRAFFIC PAINT TEST REPORT

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation: Yellow WB TM1252		Supplier: Sherwin William							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
B26	DM0662HY	1.619	80.3	77.6	59.3	3.7	Jun-27	Jul-9	Ledcor Alberta limited (kody) Hwy 733 : 2(Twp. Rd. 742-Twp Rd. 724) CMA 504
TM1252		Tolerance Limits							
		1.644	76.6	78.5	60.3				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.694	81.6	80.5	62.3				
Lower Limit		1.594	71.6	76.5	58.3				

* Indicates result outside tolerance limits.



Test not Required by AT

PER: _____ Jul-18
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 436-2152
 Fax +1 (780) 377-3599

Formulation:		Supplier: Sherwin Willian							
Yellow WB TM1252		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
B60	DM0602PW	1.621	75.2	76.1*	57.5*	3.7	Jul-11	Aug-3	Ledcor Carrot Creek Tower Rd /16 Sampled By D. Farr 780-712-3372
TM1252		Tolerance Limits							
		1.644	76.6	78.5	60.3				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.694	81.6	80.5	62.3				
Lower Limit		1.594	71.6	76.5	58.3				

* Indicates result outside tolerance limits.



Test not Required by AT

PER:  Sep-12
 DATE

Reviewed By: 

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

