

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation:		Supplier: <b>Sherwin Willian</b>							
White WB TM2153		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
<b>B25</b>	DM1302KW	1.652	79.5	77.4	60.7	3.4	Jun-27	Jul-9	Ledcor Alberta limited (kody) Hwy 733 : 2(Twp. Rd. 742-Twp Rd. 724) CMA 504
Tolerance Limits									
<b>2021</b>	<b>TM2153</b>	<b>1.681</b>	<b>77</b>	<b>78.9</b>	<b>62.4</b>				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.731	82	80.9	64.4				
Lower Limit		1.631	72	76.9	60.4				

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ Jul-18  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation: White WB TM2153		Supplier: <b>Sherwin Willian</b>							
		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
<b>B39</b>	DM1402XG	1.671	81.3	77.6	60.0	Jan-3	Jul-12	Jul-18	Ledcor Hwy 16 WB Samper D. Farr 780-712-3372
Tolerance Limits									
<b>2021</b>	<b>TM2153</b>	<b>1.681</b>	<b>77</b>	<b>78.9</b>	<b>62.4</b>				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.731	82	80.9	64.4				
Lower Limit		1.631	72	76.9	60.4				

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER:  Aug-15  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation:		Supplier: <b>Sherwin William</b>							
White WB TM2153		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
<b>B59</b>	DM0632JM	1.682	82.0	77.8	61.0	3.6	Jul-11	Aug-3	Ledcor Carrot Creek Tower Rd /16 Sampled By D. Farr 780-712-3372
Tolerance Limits									
<b>2021</b>	<b>TM2153</b>	<b>1.681</b>	<b>77</b>	<b>78.9</b>	<b>62.4</b>				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.731	82	80.9	64.4				
Lower Limit		1.631	72	76.9	60.4				

\* Indicates result outside tolerance limits.  
 Test not Required by AT

PER:  Sep-12  
 DATE  
 Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

