

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16450




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: Amec Foster Wheeler Environment & Infrastructure  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation:		Supplier: <b>Sherwin Willian</b>							
White N/A		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Touch	Date Sampled	Date Received	Applicator and Location
<b>B52</b>	275TM2378	1.678	87.3	79.4	63.2	3.2	Jul-13	Jul-14	Main Roads Hwy 2:24 & 26
<b>Tolerance Limits</b>									
Tolerance Limits									
Upper Limit									
Lower Limit									

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER:  Jul-27  
 DATE

Reviewed By: 

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.