

**TRAFFIC PAINT TEST REPORT**

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
Technical Standards Branch  
2nd Floor, Twin Atria Building  
4999 - 98 Ave  
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc  
5671 - 70 Street  
Edmonton, AB  
Canada T6B 3P6  
Tel +1 (780) 436-2152  
Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
White Acetone 986061		Tests Required							
Lab	Batch	Relative	Viscosity	Non-	Pigment	Dry to	Date	Date	Applicator and Location
Sample Number	Number	Density		Volatile	Content	Traffic	Sampled	Received	
	2025	(25/25°C)	(Krebs)	Content (%)	(%)	(Minutes)	2025	2025	
B3	CPP2410W1049	1.730	84.7	74.7	56.8	8.9	May-28	May-29	Lafrentz Hwy4, 28:02 and 37:04 Con#17549
Tolerance Limits									
986061		N/A	N/A	N/A	N/A	N/A			
Tolerance Limits			± 5	± 2% absolute	± 2% absolute				
Upper Limit			90	76.0	57.5				
Lower Limit		1.35	75	71.0	52.0				

**\*Note:**

\* Indicates result outside tolerance limits.



Test not Required by AT

PER

18-Jun-25

DATE

Reviewed By:

Reporting of these results constitutes a testing service only.  
Engineering Interpretation or evaluation of the test results is provided only on written request.