

TRAFFIC PAINT TEST REPORT

Project No.: EA16450

WSP

Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

Formulation:		Supplier: PPG							
Yellow Acetone 986063		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location
B4	2025 CPP2410Y1060	1.417	80.8	74.8	53.0	8.5	May-28	May-28	Lafrentz Hwy4, 28:02 and 37:04 Con#17549
Tolerance Limits									
986063		N/A	N/A	N/A	N/A	N/A			
Tolerance Limits				± 2% absolute	± 2% absolute				
Upper Limit		1.45	90	75.0	55.0				
Lower Limit		1.32	75	70.0	49.0				

*Note:

* Indicates result outside tolerance limits.



Test not Required by AT

PER:

18-Jun-25

DATE

Reviewed By:

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.