

TRAFFIC PAINT TEST REPORT

Project No.: EA16450



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation
Technical Standards Branch
2nd Floor, Twin Atria Building
4999 - 98 Ave
Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc
5671 - 70 Street
Edmonton, AB
Canada T6B 3P6
Tel +1 (780) 436-2152
Fax +1 (780) 377-3599

| Formulation: | | Supplier: PPG | | | | | | | |
|----------------------|--------------|------------------|-----------|----------------------|-----------------|----------------|--------------|---------------|-----------------------------------|
| Yellow WB EF-62-0139 | | Tests Required | | | | | | | |
| Lab Sample Number | Batch Number | Relative Density | Viscosity | Non-Volatile Content | Pigment Content | Dry to Traffic | Date Sampled | Date Received | Applicator and Location |
| | 2025 | (25/25°C) | (Krebs) | (%) | (%) | (Minutes) | 2025 | 2025 | |
| B2 | CPP2504Y0300 | 1.576 | 73.8 | 78.0 | 58.9 | 11.7 | May-16 | May-23 | Hwy 39:10 and Hwy795:06 Con#19883 |
| Tolerance Limits | | | | | | | | | |
| 2023 | EF-62-0139 | 1.576 | 78.6 | 77.3 | 55.4 | 13.1 | | | |
| Tolerance Limits | | ± 0.05 | ± 5 | ± 2% absolute | ± 2% absolute | 20 max. | | | |
| Upper Limit | | 1.626 | 83.6 | 79.3 | 57.4 | 20 max. | | | |
| Lower Limit | | 1.526 | 73.6 | 75.3 | 53.4 | N/A | | | |

Note:

* Indicates result outside tolerance limits.



Test not Required by AT

PER:  3-Jun-25
DATE
Reviewed By: _____

Reporting of these results constitutes a testing service only.
Engineering Interpretation or evaluation of the test results is provided only on written request.