

**TRAFFIC PAINT TEST REPORT**

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>								
White WB 801182/17251B		Tests Required								
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location	
	2024	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2024	2024		
<b>B11</b>	378817	1.623	78.0	75.3	61.6	9.6	Jun-5	Jun-11	Emcon Hwy 63:04 Sampler Athur Kavulok 780-675-2780	
<b>Tolerance Limits</b>										
<b>2023</b>	<b>801182/17251B</b>	<b>1.663</b>	<b>82</b>	<b>75.7</b>	<b>62.8</b>	<b>8.2</b>				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute					
Upper Limit		1.713	87	77.7	64.8	20 max.				
Lower Limit		1.613	77	73.7	60.8	N/A				

\* Indicates result outside tolerance limits.

Test not Required by AT

PER: \_\_\_\_\_ **2-Jul-25**  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

Formulation:		Supplier: <b>OZARK</b>							
White WB 801182/17251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location
<b>B27</b>	382709	1.619	78.4	75.4	61.7	9.3	Jul-2	Jul-3	Lafrentz Hwy 56:16 Con#23732
<b>B29</b>	382708	1.623	77.4	76.1	61.5	9.3	Jun-23	Jul-4	Emcon Hwy 2:38/2:40 Sampler Athur Kavulok 780-675-2780
Tolerance Limits									
<b>2023</b>	<b>801182/17251B</b>	<b>1.663</b>	<b>82</b>	<b>75.7</b>	<b>62.8</b>	<b>8.2</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8	20 max.			
Lower Limit		1.613	77	73.7	60.8	N/A			

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ 14-Jul-25

DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
White WB 801182/17251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled 2025	Date Received 2025	Applicator and Location
<b>B33</b>	360771	1.647	78.2	77.7	61.7	9.7	Jul-5	Jul-8	Volker Stevin Hwy 3:16
<b>B39</b>	378820	1.632	78.4	75.4	61.4	9.8	Jul-4	Jul-14	Emcon Hwy 21:24
<b>Tolerance Limits</b>									
<b>2023</b>	<b>801182/17251B</b>	<b>1.663</b>	<b>82</b>	<b>75.7</b>	<b>62.8</b>	<b>8.2</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8	20 max.			
Lower Limit		1.613	77	73.7	60.8	N/A			

\* Indicates result outside tolerance limits.

Test not Required by AT

PER: \_\_\_\_\_ **22-Jul-25**  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
White WB 801182/17251B		Tests Required							
Lab Sample Number	Batch Number 2025	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled 2025	Date Received 2025	Applicator and Location
<b>B45</b>	364289	1.614	78.2	75.6	61.7	10.0	Jul-15	Jul-17	Lafrentz Hwy 53:12 Con#23732
Tolerance Limits									
<b>2023</b>	<b>801182/17251B</b>	<b>1.663</b>	<b>82</b>	<b>75.7</b>	<b>62.8</b>	<b>8.2</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8	20 max.			
Lower Limit		1.613	77	73.7	60.8	N/A			

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **28-Jul-25**  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16335




Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
White WB 801182/17251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location
	2025	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2025	2025	
<b>B49</b>	378825	1.594*	74.8*	73.8	60.3*	14.9	Jul-22	Jul-24	Emcon Vermillion Shop( Yard)
<b>Tolerance Limits</b>									
<b>2023</b>	<b>801182/17251B</b>	<b>1.663</b>	<b>82</b>	<b>75.7</b>	<b>62.8</b>	<b>8.2</b>			
Tolerance Limits		± 0.05	± 5	± 2%	± 2%				
Upper Limit		1.713	87	absolute	absolute	20 max.			
Lower Limit		1.613	77	73.7	60.8	N/A			

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **5-Aug-25**  
 DATE

Reviewed By:  \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
White WB 801182/17251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location
	2025	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2025	2025	
<b>B59</b>	378825	1.649	81.2	76.3	62.3	8.7	Jul-29	Aug-1	Emcon Vermillion Shop( Yard)
Tolerance Limits									
<b>2023</b>	<b>801182/17251B</b>	<b>1.663</b>	<b>82</b>	<b>75.7</b>	<b>62.8</b>	<b>8.2</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8	20 max.			
Lower Limit		1.613	77	73.7	60.8	N/A			

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **11-Aug-25**  
 DATE

Reviewed By:  \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16335




Attn: Rishi Adhikari, P.Eng.

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

Formulation:		Supplier: <b>OZARK</b>							
White WB 801182/17251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location
	2025	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2025	2025	
<b>B71</b>	364281	1.653	80.1	75.8	61.8	8.7	Jul-23	Aug-14	Volker Stevin Hwy 2:06 &08 ForMacleod
Tolerance Limits									
<b>2023</b>	<b>801182/17251B</b>	<b>1.663</b>	<b>82</b>	<b>75.7</b>	<b>62.8</b>	<b>8.2</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8	20 max.			
Lower Limit		1.613	77	73.7	60.8	N/A			

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **26-Aug-25**  
 DATE

Reviewed By:  \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
White WB 801182/17251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location
	2025	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2025	2025	
<b>B73</b>	372017	1.670	81.5	76.4	62.5	8.3	Aug-11	Aug-14	Volker Stevin Hwy 22:06 Pincher Greek, AB CMA 522
Tolerance Limits									
<b>2023</b>	<b>801182/17251B</b>	<b>1.663</b>	<b>82</b>	<b>75.7</b>	<b>62.8</b>	<b>8.2</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8	20 max.			
Lower Limit		1.613	77	73.7	60.8	N/A			

\* Indicates result outside tolerance limits.

Test not Required by AT

PER: \_\_\_\_\_ **2-Sep-25**  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16335



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
White WB 801182/17251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location
	2025	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2025	2025	
<b>B83</b>	397931	1.657	78.2	75.3	61.4	8.6	Aug-12	Aug-26	Emcon Vermillion Hwy 16:22
<b>B85</b>	397931	1.643	78.2	75.3	61.4	8.6	Aug-12	Aug-26	Emcon Vermillion Hwy 16:22
<b>B87</b>	397931	1.626	77.0	74.9	61.3	8.9	Aug-25	Aug-27	Emcon Hwy 55:14Km 662-15.15 CMA 8
<b>B89</b>	359878	1.631	80.8	76.2	62.1	1.8	Aug-26	Aug-28	Line West Hwy 26:08 Drumheller Con#24974
<b>Tolerance Limits</b>									
<b>2023</b>	<b>801182/17251B</b>	<b>1.663</b>	<b>82</b>	<b>75.7</b>	<b>62.8</b>	<b>8.2</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8	20 max.			
Lower Limit		1.613	77	73.7	60.8	N/A			

\* Indicates result outside tolerance limits.

Test not Required by AT

PER: \_\_\_\_\_ **9-Sep-25**  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16335




Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: OZARK								
White WB 801182/17251B		Tests Required								
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled 2025	Date Received 2025	Applicator and Location	
B93	372016	1.650	82.8	76.2	62.1	8.7	Sep-2	Aug-25	Volker Stevin Hwy 62:02 Carston	
B95	364282	1.655	80.4	75.6	62.6	8.7	Sep-2	Aug-14	Volker Stevin Hwy 529:04 Vulcan	
<b>Tolerance Limits</b>										
2023	801182/17251B	1.663	82	75.7	62.8	8.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute					
Upper Limit		1.713	87	77.7	64.8	20 max.				
Lower Limit		1.613	77	73.7	60.8	N/A				

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **15-Sep-25**

Reviewed By: \_\_\_\_\_ **DATE**

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.