

**TRAFFIC PAINT TEST REPORT**

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.


Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location
	<b>2025</b>	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2025	2025	
<b>B12</b>	378864	1.637	80.8	77.3	61.6	8.5	Jun-5	Jun-11	Emcon Hwy 63:04 Sampler Athur Kavulok 780-675-2780
<b>Tolerance Limits</b>									
<b>2023</b>	<b>801185/27251B</b>	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **2-Jul-25**  
 DATE

Reviewed By:  \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599  
 Tel +1 (780) 436-2152  
 Fax +1 (780) 377-3599

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location
	<b>2025</b>						2025	2025	
<b>B28</b>	364303	1.620	77.2	76.8	61.5	8.9	Jul-2	Jul-3	Lafrentz Hwy 56:16 Con#23732
<b>B30</b>	364282	1.630	82.3	77.3	62.2	8.6	Jun-23	Jul-4	Emcon Hwy 2:38/2:40 Sampler Athur Kavulok 780-675-2780
<b>Tolerance Limits</b>									
<b>2023</b>	<b>801185/27251B</b>	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.

Test not Required by AT

PER: \_\_\_\_\_ **14-Jul-25**  
 DATE

Reviewed By:

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.


Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location
	<b>2025</b>						2025	2025	
<b>B34</b>	378866	1.647	80.1	77.1	61.9	8.5	Jul-5	Jul-8	Volker Stevin Hwy 3:16
<b>B40</b>	379696	1.636	79.1	77.0	61.7	8.9	Jul-4	Jul-14	Emcon Hwy 21:24
<b>Tolerance Limits</b>									
<b>2023</b>	<b>801185/27251B</b>	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **22-Jul-25**  
 DATE

Reviewed By:  \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.


Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: OZARK							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location
<b>B46</b>	2025 397938	1.613	78.2	77.3	61.9	9.1	Jul-15	Jul-17	Lafrentz Hwy 53:12 Con#23732
Tolerance Limits									
<b>2023</b>	801185/27251B	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **28-Jul-25**  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: OZARK							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location
<b>B50</b>	397939	1.624	81.3	77.5	62.1	8.7	Jul-22	Jul-24	Emcon Vermillion Shop( Yard)
Tolerance Limits									
<b>2023</b>	801185/27251B	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ **5-Aug-25**  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.


Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location
<b>B60</b>	<b>2025</b> 379699	1.611	78.4	77.1	61.5	9.1	Jul-29	Aug-1	Emcon Vermillion Shop( Yard)
Tolerance Limits									
<b>2023</b>	<b>801185/27251B</b>	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **11-Aug-25**  
 DATE

Reviewed By:  \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.


To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

Formulation:		Supplier: <b>OZARK</b>								
Yellow WB 801185/27251B		Tests Required								
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location	
<b>B72</b>	350009	1.647	79.1	77.2	61.6	9.4	Jul-23	Aug-14	Volker Stevin Hwy 2:06 &08 ForMacleod	
<b>Tolerance Limits</b>										
<b>2023</b>	801185/27251B	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute					
Upper Limit		1.702	87.5	78.3	62.8	20 max.				
Lower Limit		1.602	77.5	74.3	58.8	N/A				

\*Note:

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **26-Aug-25**  
 DATE

Reviewed By:  \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location
<b>B74</b>	364301	1.651	79.5	76.7	61.5	8.9	Aug-11	Aug-14	Volker Stevin Hwy 22:06 Pincher Greek, AB CMA 522
Tolerance Limits									
<b>2023</b>	<b>801185/27251B</b>	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **2-Sep-25**  
 DATE

Reviewed By:  \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location
	<b>2025</b>	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2025	2025	
<b>B84</b>	364297	1.614	78.8	76.8	61.4	9.1	Aug-12	Aug-26	Emcon Vermillion Hwy 16:22
<b>B86</b>	364297	1.643	77.6	76.8	62.2	8.9	Aug-12	Aug-26	Emcon Vermillion Hwy 16:22
<b>B88</b>	397941	1.610	78.2	76.9	62.2	9.0	Aug-25	Aug-27	Emcon Hwy 55:14Km 662-15.15 CMA 8
<b>B90</b>	359880	1.553*	79.0	77.1	60.0	9.3	Aug-26	Aug-28	Line West Hwy 26:08 Drumheller Con#24974
<b>Tolerance Limits</b>									
<b>2023</b>	<b>801185/27251B</b>	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ **9-Sep-25**  
 DATE  
 Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: 16450



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled 2025	Date Received 2025	Applicator and Location
<b>B94</b>	378860	1.671	87.4	78.1	62.1	8.5	Sep-2	Aug-25	Volker Stevin Hwy 62:02 Carston
<b>B96</b>	060424Y0105	1.661	79.5	77.1	61.7	8.5	Sep-2	Aug-14	Volker Stevin Hwy 529:04 Vulcan
<b>Tolerance Limits</b>									
<b>2023</b>	<b>801185/27251B</b>	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ **15-Sep-25**  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.