

TRAFFIC PAINT TEST REPORT

Project No.: CA0070980.7222



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 818-5351
 Tel +1 (780) 818-5355

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Formulation:		Supplier: OZARK								
White WB 801182/17251B		Tests Required								
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location	
	2026	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2026	2026		
B1	541232	1.622	79.5	75.3	61.4	8.8	May-19	May-25	Emcon CMA518	
B5	521333	1.652	80.3	75.5	61.5	8.7	May-12	May-26	Volker Stevin Pincher Greek CMA 523	
Tolerance Limits										
2023	801182/17251B	1.663	82	75.7	62.8	8.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute					
Upper Limit		1.713	87	77.7	64.8	20 max.				
Lower Limit		1.613	77	73.7	60.8	N/A				

* Indicates result outside tolerance limits.

Test not Required by AT

PER: _____ **29-May-26**
 DATE
 Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: CA0070980.7222



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 818-5351
 Tel +1 (780) 818-5355

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Formulation:		Supplier: OZARK							
White WB 801182/17251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled 2026	Date Received 2026	Applicator and Location
B13	524631	1.618	80.4	75.6	61.7	8.9	May-21	May-28	Emcon Vermilion CMA 15/512
B15	541227	1.610	79.9	75.7	61.6	9.2	May-28	May-28	Emcon Vermilion CMA 15/512
Tolerance Limits									
2023	801182/17251B	1.663	82	75.7	62.8	8.2			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.713	87	77.7	64.8	20 max.			
Lower Limit		1.613	77	73.7	60.8	N/A			

* Indicates result outside tolerance limits.

Test not Required by AT

PER: _____ **4-Jun-26**
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.

TRAFFIC PAINT TEST REPORT

Project No.: CA0070980.7222




Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc
 5671 - 70 Street
 Edmonton, AB
 Canada T6B 3P6
 Tel +1 (780) 818-5351
 Tel +1 (780) 818-5355

To: Alberta Transportation
 Technical Standards Branch
 2nd Floor, Twin Atria Building
 4999 - 98 Ave
 Edmonton, AB T6B 2X3

Formulation:		Supplier: OZARK								
White WB 801182/17251B		Tests Required								
Lab Sample Number	Batch Number	Relative Density	Viscosity	Non-Volatile Content	Pigment Content	Dry to Traffic	Date Sampled	Date Received	Applicator and Location	
	2026	(25/25°C)	(Krebs)	(%)	(%)	(Minutes)	2026	2026		
B19	541233	1.629	81.1	75.4	61.4	8.8	Jun-9	Jun-10	Emcon Hwy 56 CMA16	
Tolerance Limits										
2023	801182/17251B	1.663	82	75.7	62.8	8.2				
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute					
Upper Limit		1.713	87	77.7	64.8	20 max.				
Lower Limit		1.613	77	73.7	60.8	N/A				

* Indicates result outside tolerance limits.

 Test not Required by AT

PER: _____ **12-Jun-26**
 DATE

Reviewed By: _____

Reporting of these results constitutes a testing service only.
 Engineering Interpretation or evaluation of the test results is provided only on written request.