

**TRAFFIC PAINT TEST REPORT**

Project No.: CA0070980.7222



Attn: Rishi Adhikari, P.Eng.

Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location
	<b>2026</b>						2026	2026	
<b>B2</b>	524635	1.613	79.9	77.2	61.6	8.7	May-19	May-25	Emcon CMA518
<b>B6</b>	498533	1.654	79.9	77.4	61.6	8.4	May-12	May-26	Volker Stevin Pincher Greek CMA 523
<b>Tolerance Limits</b>									
<b>2023</b>	<b>801185/27251B</b>	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.



Test not Required by AT

PER: \_\_\_\_\_ **29-May-26**

DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: CA0070980.7222



Attn: Rishi Adhikari, P.Eng.


Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled	Date Received	Applicator and Location
	<b>2026</b>						2026	2026	
<b>B14</b>	523289	1.625	80.6	77.3	77.3	8.6	May-21	May-28	Emcon Vermilion CMA 15/512
<b>B16</b>	422252	1.603	77.7	76.8	76.8	9.2	May-28	May-28	Emcon Vermilion CMA 15/512
<b>Tolerance Limits</b>									
<b>2023</b>	<b>801185/27251B</b>	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **4-Jun-26**  
 DATE

Reviewed By:  \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.

**TRAFFIC PAINT TEST REPORT**

Project No.: CA0070980.7222



Attn: Rishi Adhikari, P.Eng.


Distribution Addressee: WSP Canada Inc  
 5671 - 70 Street  
 Edmonton, AB  
 Canada T6B 3P6  
 Tel +1 (780) 818-5351  
 Tel +1 (780) 818-5355

To: Alberta Transportation  
 Technical Standards Branch  
 2nd Floor, Twin Atria Building  
 4999 - 98 Ave  
 Edmonton, AB T6B 2X3

Formulation:		Supplier: <b>OZARK</b>							
Yellow WB 801185/27251B		Tests Required							
Lab Sample Number	Batch Number	Relative Density (25/25°C)	Viscosity (Krebs)	Non-Volatile Content (%)	Pigment Content (%)	Dry to Traffic (Minutes)	Date Sampled 2026	Date Received 2026	Applicator and Location
<b>B20</b>	524637	1.630	80.6	77.2	61.6	8.5	Jun-9	Jun-10	Emcon Hwy 56 CMA16
Tolerance Limits									
<b>2023</b>	<b>801185/27251B</b>	<b>1.652</b>	<b>82.5</b>	<b>76.3</b>	<b>60.8</b>	<b>8.3</b>			
Tolerance Limits		± 0.05	± 5	± 2% absolute	± 2% absolute				
Upper Limit		1.702	87.5	78.3	62.8	20 max.			
Lower Limit		1.602	77.5	74.3	58.8	N/A			

\*Note:

\* Indicates result outside tolerance limits.

 Test not Required by AT

PER: \_\_\_\_\_ **12-Jun-26**  
 DATE

Reviewed By: \_\_\_\_\_

Reporting of these results constitutes a testing service only.  
 Engineering Interpretation or evaluation of the test results is provided only on written request.